

**TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371**

10/088376

| | | |
|--|---|--|
| ATTORNEY DOCKET NUMBER IN-5562 | U.S. APPLICATION NO (IF KNOWN SEE 37 RR 15) | |
| INTERNATIONAL APPLICATION NO. PCT/EP00/08503 | INTERNATIONAL FILING DATE 31 August 2000 (31.08.2000) | PRIORITY DATE CLAIMED 23 September 1999 (23.09.1999) |

TITLE OF INVENTION: **USE OF ASSOCIATIVE THICKENERS BASED ON POLYURETHANE AND/OR DIPROPYLENE GLYCOL MONOALKYL ETHERS IN COLOURED AND/OR DECORATIVE EFFECT MULTI-LAYERED LACQUERS**

APPLICATION(S) FOR DO/EO/US: **Ines MANGELS, Karl-Heinz JOSTEN, Udo NENNER, Egon WEGNER, Ekkehard SAPPER and Nicola ZARSE**

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371 (b) and PCT Articles 22 and 39(1).
4. ☐ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☐ are transmitted herewith (required only if not transmittal by the International Bureau).
 - b. ☒ have been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US)
6. ☒ A translation of the International Application into English (35 U.S.C. 371(C)(2)).
7. ☒ Amendment to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made
8. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ A translation of the annex to the International Preliminary Examination Report under PCT Article 36

Items 11. to 16. below concern other document(s) or information included:

11. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included
13. ☒ A FIRST preliminary amendment.
☐ A SECOND or SUBSEQUENT preliminary amendment.
14. ☐ A substitute specification.
15. ☐ A Change of power of attorney and/or address letter.
16. ☒ Other items or information:

A copy of the cover sheet from the PCT Published Application
A copy of the cover sheet from the Priority Document

I hereby certify that the attached correspondence is being deposited with the United States Postal Service in an envelope as "Express Mail Post Office to Addressee" Mailing Label No. **E1973 679 288US** addressed to the Commissioner for Patents, Washington, DC 20231 on March 11, 2002.

Marjorie E. Ellis
Marjorie Ellis

| | | | |
|---|--------------|---|-----------------|
| U.S. APPLICATION NO. (if known) 10/088376 INTERNATIONAL APPLICATION NO. PCT/EP00/08503 | | ATTORNEY'S DOCKET NUMBER IN-5562 | |
| 17. <input checked="" type="checkbox"/> The following fees are submitted | | CALCULATIONS PTO USE ONLY | |
| Basic National Fee (37 CFR 1.492(a)(1)-(5)): Neither international preliminary examination fee (37 CFR 1.482) Nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO..... | | \$970.00 | |
| International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO..... | | \$890.00 | |
| International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.44(a)(2)) paid to USPTO..... | | \$690.00 | |
| International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4)..... | | \$670.00 | |
| International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) | | \$ 96.00 | |
| ENTER APPROPRIATE BASIC FEE AMOUNT = | | \$890.00 | |
| Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)). | | \$ | |
| Claims | Number Filed | Number Extra | Rate |
| Total Claims | 18 - 20 = | 0 | X \$ 18.00 |
| Independent claims | 02 - 03 = | 0 | X \$ 84.00 |
| Multiple dependent claims(s) (if applicable) | | | + \$280.00 |
| TOTAL OF ABOVE CALCULATION = | | | \$890.00 |
| Reduction by 1/2 for filing by small entity, if applicable. Verified Small Entity statement must also be filed. (Note 37 CFR 1.9, 1.27, 1.28). | | | \$ |
| SUBTOTAL = | | | \$890.00 |
| Processing fee of \$130.00 for furnishing the English translation later the months from the earliest claimed priority date (37 CFR 1.492(f)). | | | \$ |
| TOTAL NATIONAL FEE = | | | \$890.00 |
| Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property + | | | \$ 40.00 |
| TOTAL FEES ENCLOSED = | | | \$930.00 |
| Amount to be: refunded | | | \$ |
| Charged | | | \$930.00 |
| a. <input type="checkbox"/> A check in the amount of \$_____ to cover the above fees is enclosed. | | | |
| b. <input checked="" type="checkbox"/> Please charge my Deposit Account No. 23-3425 in the amount of \$930.00 to cover the above fees A triplicate copy of this sheet is enclosed. | | | |
| c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 23-3425 . A triplicate copy of this sheet is enclosed. | | | |
| NOTE: Where an appropriate time limit under 37 CFR 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status. | | | |
| SEND ALL CORRESPONDENCE TO: BASF CORPORATION Patent Department 26701 Telegraph Road Southfield, Michigan 48034-2442 (248) 948-2355 Customer No. 26922 | | SIGNATURE Michael F. Morgan Name 42,906 REGISTRATION NUMBER | |

Patent Application Data Sheet

10/088376

IC10 REC'D PCT/PTC 11 MAR 2002¹

| | |
|---|--|
| Title Line One:: Title Line Two:: Title Line Three:: Title Line Four:: Title Line Five:: | USE OF ASSOCIATIVE THICKENERS BASED ON POLYURETHANE AND/OR DIPROPYLENE GLYCOL MONOALKYL ETHERS IN COLOURED AND/OR DECORATIVE EFFECT MULTI-LAYERED LACQUERS |
| Total Drawing Sheets:: Formal Drawings?:: Application Type:: Application Filing Date:: Docket Number:: | Utility Monday, March 11, 2002 IN-5562 |
| Representative Information:: | BASF Corporation Patent Department 26701 Telegraph Road Southfield, Michigan 48034 |
| Attorney(s) Name:: Registration Number:: Attorney(s) Name:: Registration Number:: Attorney(s) Name:: Registration Number:: | Anne Gerry Sabourin 33,772 Mary E. Golota 36,814 Michael F. Morgan 42,906 |
| Representative Customer Number:: | 26922 |
| Continuity Information This application is a National Phase of >Application One:: Filing Date:: | PCT/EP00/08503 31 August 2000 |
| Inventor One Given Name:: Family Name:: Street:: City:: Country:: Postal or Zip Code:: Citizenship Country:: | Ines MANGELS Pinienweg 21 48165 Münster Federal Republic of Germany German |
| Inventor Two Given Name:: Family Name:: Street:: City:: Country:: Postal or Zip Code:: Citizenship Country:: | Karl-Heinz JOSTEN Brusseler Str. 8 97209 Veitshöchheim Federal Republic of Germany German |
| Inventor Three Given Name:: Family Name:: Street:: City:: Country:: Postal or Zip Code:: Citizenship Country:: | Udo NENNER Am Mühlacker 3 97877 Wertheim Federal Republic of Germany German |

| | |
|---|--|
| Inventor Four Given Name:: Family Name:: Street:: City:: Country:: Postal or Zip Code:: Citizenship Country:: | Egon WEGNER Martinstr. 8 97209 Veitshöchheim Federal Republic of Germany German |
| Inventor Five Given Name:: Family Name:: Street:: City:: Country:: Postal or Zip Code:: Citizenship Country:: | Ekkehard SAPPER Austr. 55 97222 Rimpar Federal Republic of Germany German |
| Inventor Six Given Name:: Family Name:: Street:: City:: Country:: Postal or Zip Code:: Citizenship Country:: | Nicola ZARSE Steinkamp 3a 48165 Münster Federal Republic of Germany German |
| Prior Foreign Applications Foreign Application One:: Filing Date:: Country:: Priority Claimed:: | 199 45 574.0 23 September 1999 Germany yes |

10/088376

JC10 Recd F01-70 11 MAR 2002

PATENT
(Practitioner's Docket No. IN-5562)

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of

Ines MANGELS, Karl-Heinz JOSTEN, Udo
NENNER, Egon WEGNER, Ekkehard
SAPPER and Nicola ZARSE

Serial No.: This application is a National
Phase of Patent Application PCT/EP00/08503
filed 31 August 2000.


Filed: Monday, March 11, 2002

For: USE OF ASSOCIATIVE
THICKENERS BASED ON
POLYURETHANE AND/OR
DIPROPYLENE GLYCOL MONOALKYL
ETHERS IN COLOURED AND/OR
DECORATIVE EFFECT MULTI-LAYERED
LACQUERS

Group Art Unit: Not Assigned

Examiner: Not Assigned

I hereby certify that the attached correspondence is
being deposited with the United States Postal Service in
an envelope as "Express Mail Post Office to Addressee"
Mailing Label No. **ET973 679 288US** addressed to the
Assistant Commissioner for Patents, Washington, D.C.
20231 on March 11, 2002.



Marjorie Ellis

PRELIMINARY AMENDMENT UNDER 37 CFR § 1.115

Commissioner for Patents

Washington, D.C. 20231

Dear Sir:

This preliminary amendment is submitted with the application for entry into the U.S.
National Phase under Chapter II. This application is based on PCT/EP00/08503 filed on 31
August 2000.

In connection with the filing of this National Phase application, please make the
following preliminary amendments.

IN THE SPECIFICATION

After the title, please insert --This application is a National Phase Application of
Patent Application **PCT/EP00/08503** filed on 31 August 2000.--

IN THE CLAIMS:

Please cancel claims 1-23.

Please add claims 24-41.

24. (New) A method for suppressing optical defects in a paint system, wherein the paint system is one of a multicoat color paint system, a multicoat effect paint system, a multicoat color and effect paint system, a color refinish paint system, an effect refinish paint system, and a color and effect refinish paint system, comprising including an associative thickener in the paint system, wherein the associative thickener is at least one of a polyurethane-based associative thickener and a dipropylene glycol monoalkyl ether.
25. (New) The method of claim 24, wherein the paint system comprises at least one basecoat layer and at least one clearcoat layer.
26. (New) The method of claim 25, wherein the basecoat layer is produced from an aqueous basecoat material.
27. (New) The method of claim 26, wherein the aqueous basecoat material comprises a polyurethane polymer.
28. (New) The method of claim 24, wherein the associative thickener is present in a basecoat layer.
29. (New) The method of claim 24, wherein the polyurethane-based associative thickener and the dipropylene glycol monoalkyl ether are present in a basecoat layer.
30. (New) The method of claim 24, wherein the optical defects comprise at least one of:
- i) light-colored spots, introduced by at least one of dried-up liquid residues and abrasion dust residues, which remain after abrading of defects in the paint system or in a surfacer that is to be coated with the paint system; and
 - ii) polishing spots, induced by the polishing of defects in the paint system, which is performed for the purpose of refinishing the paint system.


31. (New) The method of claim 26, wherein the aqueous basecoat material comprises
- (A) at least one water-soluble or -dispersible polyurethane,
 - (B) at least one crosslinking agent,
 - (C) at least one pigment that is at least one of a color pigment, an effect pigment, and a color and effect pigment,
 - (D) at least one neutralizing agent,
 - (E) at least one inorganic thickener,
 - (F) an associative thickener that is at least one of a dipropylene glycol monoalkyl ether and a polyurethane-based associative thickener,
 - (G) optionally, at least one water-soluble or -dispersible polyacrylate resin prepared in the presence of a water-soluble or -dispersible polyurethane, and
 - (H) optionally, at least one water-soluble or -dispersible polyester resin.
32. (New) The method of claim 31, wherein the aqueous basecoat material, based on its overall weight, contains from 0.5 to 11% by weight of the dipropylene glycol monoalkyl ether.
33. (New) The method of claim 31, wherein the aqueous basecoat material, based on its overall weight, contains from 0.1 to 4% by weight of the polyurethane-based associative thickener.
34. (New) The method of claim 31, wherein the aqueous basecoat material further comprises at least one additive.
35. (New) The paint system prepared by the process of claim 24.
36. (New) The paint system of claim 35, wherein the paint system is one of an original coating for a motor vehicle body, an industrial coating, an electrical components coating, a coil coating, a packaging coating, a plastics coating, and a furniture coating.

37. (New) An aqueous basecoat material comprising
- (A) at least one water-soluble or -dispersible polyurethane,
 - (B) at least one crosslinking agent,
 - (C) at least one pigment that is at least one of a color pigment, an effect pigment, and a color and effect pigment,
 - (D) at least one neutralizing agent,
 - (E) at least one inorganic thickener,
 - (F) an associative thickener that is at least one of a dipropylene glycol monoalkyl ether and a polyurethane-based associative thickener,
 - (G) optionally, at least one water-soluble or -dispersible polyacrylate resin prepared in the presence of a water-soluble or -dispersible polyurethane, and
 - (H) optionally, at least one water-soluble or -dispersible polyester resin.
38. (New) The aqueous basecoat material of claim 37, wherein the aqueous basecoat material, based on its overall weight, contains from 0.5 to 11% by weight of the dipropylene glycol monoalkyl ether.
39. (New) The aqueous basecoat material of claim 37, wherein the aqueous basecoat material, based on its overall weight, contains from 0.1 to 4% by weight of the polyurethane-based associative thickener.
40. (New) The aqueous basecoat material of claim 37 further comprises at least one additive.
41. (New) A paint system comprising at least one basecoat layer; wherein the paint system is one of a multicoat color paint system, a multicoat effect paint system, a multicoat color and effect paint system, a color refinish paint system, an effect refinish paint system, and a color and effect refinish paint system; and wherein the basecoat layer is produced from the aqueous basecoat material of claim 37.

REMARKS

Upon entry of the present amendment, claims 24-41 are pending in the application. New claims 24-41 add no new matter, as these claims contain subject matter deleted from claims 1-23. There are two (2) independent claims and a total of eighteen (18) claims pending in the application. Applicants respectfully request entry of the preliminary amendment.

Respectfully Submitted,



Michael F. Morgan
Registration No. 42,906
Customer No. 26922

Date: March 11, 2002
BASF Corporation
26701 Telegraph Road
Southfield, Michigan 48034-2442
(248)-948-2355

USE OF POLYURETHANE-BASED ASSOCIATIVE THICKENERS AND/OR
DIPROPYLENE GLYCOL MONOALKYL ETHERS IN MULTICOAT COLOR
AND/OR EFFECT PAINT SYSTEMS

- 5 The present invention relates to the use of polyurethane-based associative thickeners and/or dipropylene glycol monoalkyl ethers to suppress optical defects in multicoat color and/or effect paint systems or their refinishes. The present invention also relates
- 10 to novel aqueous basecoat materials which comprise at least one polyurethane-based associative thickener and/or at least one dipropylene glycol monoalkyl ether. The present invention further relates to the use of the novel aqueous basecoat materials for producing
- 15 multicoat color and/or effect paint systems and their refinishes.

- Owing to their numerous advantageous properties, multicoat color and/or effect paint systems are
- 20 nowadays employed in many fields, examples being the coating of motor vehicle bodies, industrial components, including electrical components, coils, and packaging, and fabrics or furniture. Owing to the particularly stringent requirements on the part of automakers and
- 25 their customers, these multicoat color and/or effect paint systems have become established in particular in this field of use.

As is known, the bodies of automobiles are nowadays coated with a multicoat paint system composed of a primer, particularly an electrocoat, a surfacer or an antistonechip primer, and a multicoat color and/or effect paint system. The multicoat paint system itself is generally composed of at least one basecoat and at least one clearcoat. Advantageously, the basecoat is produced from an aqueous basecoat material. In accordance with the particularly advantageous wet-on-wet technique, the aqueous basecoat material is applied to the surfacer or the antistonechip primer and partly dried, but not crosslinked. Thereafter, at least one clearcoat film is applied to the uncured aqueous basecoat film and is cured together with the aqueous basecoat film. This technique is also employed for the refinish of the multicoat color and/or effect paint systems.

Both during the production of the multicoat color and/or effect paint systems and during the refinish of defects present therein, optical defects can occur which are manifested to disruptive effect and which give cause for complaints. These optical defects may have a variety of causes.

25

Accordingly, defects in the surfacer or in the antistonechip primer are normally removed by abrading. When this is done, abrasion dust residues in the form of fingerprints or, in the case of wet abrasion, in the

form of dried water droplets can remain. After overcoating with aqueous basecoat and clearcoat material, these "fingerprints" and/or "droplets" show up as light-colored, clearly visible sites in the
5 resulting multicoat color and/or effect paint system. These optical defects are also referred to by the skilled worker as "light spots".

10 Optical defects of this kind also arise if the clearcoat of a multicoat color and/or effect paint system is abraded for purposes of better adhesion of a refinish that is to be applied. These optical defects are also referred to by the skilled worker as "abrasion spots".

15 These pale spots are not abrasion scars which are poorly covered, but may instead be induced even by beads of sweat or the sweat on the fingers.

20 Another kind of optical defect, known as polishing spots, results if the finished multicoat color and/or effect paint system is polished at damaged sites, but then, owing to further damaged sites, has to be subjected to a complete refinish, with the polished
25 sites as well being overcoated. In the refinish, these polishing sites are very clearly visible owing to their different shade.

To date it has been possible to prevent these optical defects only by extremely careful and cautious working and a high additional cleaning effort, since the aqueous basecoat materials available at present do not
5 have the sufficient insensitivity to such defects in and on the surfacers and/or in and on the multicoat color and/or effect paint systems, and are therefore unable, or unable sufficiently, to compensate these defects optically. This fact, however, leads to
10 relatively long processing times and thus to higher costs in line finishing or in line or workshop refinish.

There is therefore a high demand for basecoat
15 materials, especially aqueous basecoat materials, which no longer have these disadvantages but instead provide optical compensation of the defects while retaining all of their other advantageous properties, if not indeed improving upon them.

20 Aqueous basecoat materials which are outstandingly suitable for producing color and/or effect paint systems are known, for example, from the German patent application DE-A-44 37 535. They comprise an inorganic
25 thickener, such as a phyllosilicate, and organic solvents, such as butyl glycol. As binders they comprise water-soluble or -dispersible polyurethanes, water-soluble or -dispersible polyacrylate resins prepared in the presence of such polyurethanes, and

water-soluble or -dispersible polyesters. They have a very high storage stability even at relatively high temperatures. The use of polyurethane-based associative thickeners and/or dipropylene glycol monoalkyl ethers is not disclosed by DE-A-44 37 535.

Polyurethane-based associative thickeners and their performance properties and advantages are known. By way of example, reference may be made here to Römpf Lexikon
10 Lacke und Druckfarben, Georg Thieme Verlag, Stuttgart, New York, 1998, "thickeners", pages 599 to 600, and the textbook "Lackadditive" [Additives for Coatings] by Johan Bieleman, Wiley-VCH, Weinheim, New York, 1998, pages 51 to 59 and 65. The use of these polyurethane-
15 based associative thickeners for suppressing optical defects in multicoat color and/or effect paint systems and their refinishes are not described therein.

It is an object of the present invention to provide
20 novel basecoat materials, especially the aqueous basecoat materials, which comprise novel combinations of constituents and which allow the production and refinish of multicoat color and/or effect paint systems without the formation of light spots or polishing
25 spots. The novel basecoat materials, particularly the novel aqueous basecoat materials, ought to continue to have the particular advantages of the existing basecoat materials or to exhibit additional, novel advantageous properties.

Found accordingly was the novel use of polyurethane-based associative thickeners and/or dipropylene glycol monoalkyl ethers for suppressing optical defects in multicoat color and/or effect paint systems and their refinishes.

In the text below, this novel use is referred to as "inventive use".

10

Additionally found was the novel aqueous basecoat material which comprises

15

(A) at least one water-soluble or -dispersible polyurethane,

20

(B) at least one crosslinking agent,

(C) at least one color and/or effect pigment,

(D) at least one neutralizing agent,

(E) at least one inorganic thickener, and

25 (F) at least one dipropylene glycol monoalkyl ether.

Additionally found was the further novel aqueous basecoat material which comprises

- (A) at least one water-soluble or -dispersible polyurethane,
- (B) at least one crosslinking agent,
- (C) at least one color and/or effect pigment,
- (D) at least one neutralizing agent,
- (E) at least one inorganic thickener,
- (G) at least one polyurethane-based associative thickener,
- (H) if desired, at least one water-soluble or -dispersible polyacrylate resin prepared in the presence of a water-soluble or -dispersible polyurethane, and
- (I) at least one water-soluble or -dispersible polyester resin.

In the text below, these novel aqueous basecoat materials are referred to collectively as "aqueous basecoat materials of the invention".

Found not least were the novel multicoat color and/or effect paint systems which comprises at least one


basecoat producible from one of the aqueous basecoat materials of the invention.

In the light of the prior art it was surprising and
5 unforeseeable for the skilled worker that the object of
the present invention could be achieved by means of the
inventive use. Even more surprising was that the
achievement of the object was demonstrably not based on
the rheological properties of the aqueous basecoat
10 materials of the invention, which in this respect are
equivalent to the known aqueous basecoat materials.
Moreover, it could not at all have been expected that
the durable suppression or prevention of polishing
spots could be achieved by the combination of the
15 polyurethane-based associative thickener (G) for
inventive use and at least one dipropylene glycol
monoalkyl ether (F).

In accordance with the invention, the polyurethane-
20 based associative thickener (G) or the dipropylene
glycol monoalkyl ether (F) can be employed alone, with
the use alone of the associative thickener (G) offering
particular advantages and therefore being preferred in
accordance with the invention. Very particular
25 advantages result, however, from the joint use of the
two constituents, which is therefore particularly
preferred in accordance with the invention.

The first inventively essential constituent of the aqueous basecoat materials of the invention is therefore at least one polyurethane-based associative thickener (G). These thickeners are normally composed of nonionic hydrophobic polymers which are available either in liquid form, as a 50 percent strength solution in water or in organic solvents, for example, or in powder form. They are based on water-soluble polyurethanes having a comparatively low molecular weight of from 10 000 to 50 000.

The water-soluble polyurethanes (G) are prepared by reacting diisocyanates, especially the diisocyanates described below, with diols, especially the diols described below, and hydrophobic blocking components, thereby resulting in the following idealized structure of the general formula I.



In the general formula I, the indices x and n stand for integers whose value is sufficient to give the molecular weights indicated above.

The radical R^1 stands for a hydrophobic aliphatic or aromatic group. Examples of suitable groups of this kind are oleyl, stearyl, dodecylphenyl or nonylphenyl.

The radical R^2 stands for a hydrophilic segment. Examples of suitable hydrophilic segments are polyesters, especially polyesters of maleic acid and ethylene glycol, and polyethers, especially
5 polyethylene glycol or its derivatives.

The polyurethane-based associative thickeners for inventive use therefore contain the three following kinds of segments or building-block groups:

10

- hydrophobic end segments,
- two or more hydrophilic segments, and

15

- urethane groups.

These segments or building-block groups can be linked to one another in a very wide variety of ways, so resulting in a very wide variety of polymer structures.

20

In accordance with the invention, however, advantageous associative thickeners are those which contain linear and comb-shaped polymer structures. It is essential that each polymer molecule contains at least two hydrophobic end segments.

25

For the preparation of the aqueous basecoat materials of the invention, the associative thickeners (G) for inventive use are employed as powders or, preferably,

as 20 to 30% strength by weight solutions in at least one water-dilutable solvent.

In the aqueous basecoat materials of the invention they
5 are advantageously present in an amount of from 0.1 to 4.0%, preferably from 0.4 to 3.5%, and in particular from 0.4 to 3.0% by weight, based in each case on the overall weight of the respective aqueous basecoat material.

10

Dipropylene glycol monoalkyl ethers are compounds which are known per se and are employed in the coatings field as solvents or as solvent additions. Examples of suitable alkyl radicals in this context are methyl,
15 propyl, isopropyl, n-butyl, n-pentyl or n-hexyl, of which the methyl radical is particularly advantageous and is therefore used with particular preference.

The dipropylene glycol methyl ether (F) used with
20 particular preference is a compound known per se or a mixture known per se, both of which are available commercially. It is derived from dipropylene glycol, 1,1'-oxybis-(2-propanol), and/or isomers thereof.

25 In the aqueous basecoat materials of the invention, the dipropylene glycol monoalkyl ethers (F) are present advantageously in an amount of from 0.5 to 11%, preferably from 1.0 to 9%, and in particular from 1.0

to 7.0% by weight, based in each case on the overall weight of the respective aqueous basecoat material.

The other essential constituent of the aqueous basecoat materials of the invention is at least one water-soluble or -dispersible polyurethane (A). Polyurethanes (A) and processes for preparing them are known per se and are described, for example, in the German patent DE-A-44 37 535.

10

Advantageously, depending on the nature of the stabilization, the polyurethane (A) for inventive use has an acid number or amine number of from 10 to 250 mg KOH/g (ionic stabilization or nonionic plus ionic stabilization) or from 0 to 10 mg KOH/g (nonionic stabilization), an OH number of from 30 to 350 mg KOH/g, and a number-average molecular weight of from 1 500 to 55 000 daltons.

20 For the preparation of the polyurethanes (A) it is conventional to use diisocyanates and also, if desired and in minor amounts, polyisocyanates, for the purpose of introducing branches. In the context of the present invention, minor amounts are amounts which do not cause
25 gelling of the polyurethanes (A) during their preparation. This may also be prevented by using small amounts of monoisocyanates as well.

Examples of suitable diisocyanates are isophorone diisocyanate (i.e., 5-isocyanato-1-isocyanatomethyl-1,3,3-trimethylcyclohexane), 5-isocyanato-1-(2-isocyanatoethyl-1-yl)-1,3,3-trimethylcyclohexane, 5-isocyanato-1-(3-isocyanatoprop-1-yl)-1,3,3-trimethylcyclohexane, 5-isocyanato-(4-isocyanatobut-1-yl)-1,3,3-trimethylcyclohexane, 1-isocyanato-2-(3-isocyanatoprop-1-yl)-cyclohexane, 1-isocyanato-2-(3-isocyanatoethyl-1-yl)-cyclohexane, 1-isocyanato-2-(4-isocyanatobut-1-yl)-cyclohexane, 1,2-diisocyanatocyclobutane, 1,3-diisocyanatocyclobutane, 1,2-diisocyanatocyclopentane, 1,3-diisocyanatocyclopentane, 1,2-diisocyanatocyclohexane, 1,3-diisocyanatocyclohexane, 1,4-diisocyanatocyclohexane, dicyclohexylmethane 2,4'-diisocyanate, trimethylene diisocyanate, tetramethylene diisocyanate, pentamethylene diisocyanate, hexamethylene diisocyanate, ethylethylene diisocyanate, trimethylhexane diisocyanate, heptanemethylene diisocyanate or diisocyanates derived from dimeric fatty acids, as marketed under the commercial designation DDI 1410 by the company Henkel and described in patents DO 97/49745 and WO 97/49747, especially 2-heptyl-3,4-bis(9-isocyanatononyl)-1-pentylcyclohexane, or 1,2-, 1,4- or 1,3-bis(isocyanatomethyl)cyclohexane, 1,2-, 1,4- or 1,3-bis(2-isocyanatoethyl-1-yl)cyclohexane, 1,3-bis(3-isocyanatoprop-1-yl)cyclohexane, 1,2-, 1,4- or 1,3-bis(4-isocyanatobut-1-yl)cyclohexane, liquid bis(4-isocyanatocyclohexyl)methane with a trans/trans content of up to 30% by weight, preferably 25% by weight, and

in particular 20% by weight, as is described in patents DE-A-44 14 032, GB-A-1 220 717, DE-A-16 18 795 or DE-A-17 93 785; tolylene diisocyanate, xylylene diisocyanate, bisphenylene diisocyanate, naphthylene diisocyanate or diphenylmethane diisocyanate.

Examples of suitable polyisocyanates are the isocyanurates of the diisocyanates described above.

10 Examples of highly suitable monoisocyanates are phenyl isocyanate, cyclohexyl isocyanate or stearyl isocyanate.

The polyurethanes (A) for inventive use are also prepared using

- saturated and unsaturated polyols of relatively high and low molecular mass, especially diols and, in minor amounts, triols for the purpose of introducing branches,

- polyamines,

- amino alcohols, and

25 - compounds which introduce stabilizing (potentially) ionic and/or nonionic functional groups.

Examples of suitable polyols are saturated or olefinically unsaturated polyester polyols which are prepared by reacting

- 5 - unsulfonated or sulfonated saturated and/or unsaturated polycarboxylic acids or their esterifiable derivatives, alone or together with monocarboxylic acids, and
- 10 - saturated and/or unsaturated polyols, alone or together with monools.

Examples of suitable polycarboxylic acids are aromatic, aliphatic and cycloaliphatic polycarboxylic acids.

- 15 Preference is given to the use of aromatic and/or aliphatic polycarboxylic acids.

Examples of suitable aromatic polycarboxylic acids are phthalic acid, isophthalic acid, terephthalic acid, 20 phthalic, isophthalic or terephthalic acid monosulfonate, or halophthalic acids, such as tetrachlorophthalic or tetrabromophthalic acid, among which isophthalic acid is advantageous and is therefore used with preference.

25

Examples of suitable acyclic aliphatic or unsaturated polycarboxylic acids are oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid,

undecanedicarboxylic acid or dodecanedicarboxylic acid, or dimeric fatty acids, or maleic acid, fumaric acid or itaconic acid, of which adipic acid, glutaric acid, azelaic acid, sebacic acid, dimeric fatty acids and
5 maleic acid are advantageous and are therefore used with preference.

Examples of suitable cycloaliphatic and cyclic unsaturated polycarboxylic acids are 1,2-cyclobutanedicarboxylic acid, 1,3-cyclobutanedicarboxylic acid,
10 1,2-cyclopentanedicarboxylic acid, 1,3-cyclopentanedicarboxylic acid, hexahydrophthalic acid, 1,3-cyclohexanedicarboxylic acid, 1,4-cyclohexanedicarboxylic acid, 4-methylhexahydrophthalic acid, tricyclodecanedicarboxylic acid, tetrahydrophthalic acid or 4-methyl-
15 tetrahydrophthalic acid. These dicarboxylic acids may be used both in their cis and in their trans form and also as a mixture of both forms.

Also suitable are the esterifiable derivatives of the abovementioned polycarboxylic acids, such as their monoesters or polyesters with aliphatic alcohols having 1 to 4 carbon atoms or hydroxy alcohols having 1 to 4 carbon atoms, for example. It is also possible to use
20 the anhydrides of the abovementioned polycarboxylic acids, where they exist.

Together with the polycarboxylic acids it is also possible if desired to use monocarboxylic acids, such


as, for example, benzoic acid, tert-butylbenzoic acid, lauric acid, isononanoic acid, fatty acids of naturally occurring oils, acrylic acid, methacrylic acid, ethacrylic acid or crotonic acid. The preferred
5 monocarboxylic acid used is isononanoic acid.

Examples of suitable polyols are diols and triols, especially diols. Normally, triols are used alongside the diols in minor amounts in order to introduce
10 branches into the polyester polyols. In the context of the present invention, minor amounts are amounts which do not cause gelling of the polyester polyols during their preparation.


15 Suitable diols are ethylene glycol, 1,2- or 1,3-propanediol, 1,2-, 1,3- or 1,4-butanediol, 1,2-, 1,3-, 1,4- or 1,5-pentanediol, 1,2-, 1,3-, 1,4-, 1,5- or 1,6-hexanediol, neopentyl hydroxypivalate, neopentyl glycol, diethylene glycol, 1,2-, 1,3- or 1,4-
20 cyclohexanediol, 1,2-, 1,3- or 1,4-cyclohexanedimethanol, trimethylpentanediol, ethylbutylpropanediol or the positionally isomeric diethyloctanediols. These diols may also be used per se for the preparation of the polyurethanes (A) for inventive use.

25

Further examples of suitable diols are diols of the formula I or II:



where R^3 and R^4 are each an identical or different radical and are an alkyl radical having 1 to 18 carbon atoms, an aryl radical or a cycloaliphatic radical, with the proviso that R^3 and/or R^4 must not be methyl;



where R^5 , R^6 , R^8 and R^9 are each identical or different radicals and are an alkyl radical having 1 to 6 carbon atoms, a cycloalkyl radical or an aryl radical and R^7 is an alkyl radical having 1 to 6 carbon atoms, an aryl radical or an unsaturated alkyl radical having 1 to 6 carbon atoms, and n is either 0 or 1.

Suitable diols I of the general formula I are all propanediols of the formula in which either R^3 or R^4 , or R^3 and R^4 , is or are not methyl, such as, for example, 2-butyl-2-ethyl-1,3-propanediol, 2-butyl-2-methyl-1,3-propanediol, 2-phenyl-2-methyl-1,3-propanediol, 2-propyl-2-ethyl-1,3-propanediol, 2-di-tert-butyl-1,3-

propanediol, 2-butyl-2-propyl-1,3-propanediol, 1-dihydroxymethylbicyclo[2.2.1]heptane, 2,2-diethyl-1,3-propanediol, 2,2-dipropyl-1,3-propanediol or 2-cyclohexyl-2-methyl-1,3-propanediol, et cetera.

5

Examples of diols II of the general formula II that may be used are 2,5-dimethyl-2,5-hexanediol, 2,5-diethyl-2,5-hexanediol, 2-ethyl-5-methyl-2,5-hexanediol, 2,4-dimethyl-2,4-pentanediol, 2,3-dimethyl-2,3-butanediol,

10 1,4-(2'-hydroxypropyl)benzene and 1,3-(2'-hydroxypropyl)benzene.

Of these diols, hexanediol and neopentyl glycol are particularly advantageous and are therefore used with
15 particular preference.

The abovementioned diols may also be used per se to prepare the polyurethanes (A) for inventive use.

20 Examples of suitable triols are trimethylolpropane, trimethylolpropane or glycerol, especially trimethylolpropane.

The abovementioned triols may also be used per se to
25 prepare the polyurethanes (A) for inventive use (cf. the patent EP-A-0 339 433).

If desired, minor amounts of monools may also be used. Examples of suitable monools are alcohols or phenols

such as ethanol, propanol, n-butanol, sec-butanol, tert-butanol, amyl alcohols, hexanols, fatty alcohols, allyl alcohol, or phenol.

- 5 The polyester polyols may be prepared in the presence of small amounts of a suitable solvent as entrainer. Examples of entrainers used are aromatic hydrocarbons, such as especially xylene and (cyclo)aliphatic hydrocarbons, e.g., cyclohexane or methylcyclohexane.

10

Further examples of suitable polyols are polyester diols which are obtained by reacting a lactone with a diol. They are notable for the presence of terminal hydroxyl groups and repeating polyester fractions of

15 the formula $-(-\text{CO}-(\text{CHR}^{10})_m-\text{CH}_2-\text{O})-$. Here, the index m is preferably from 4 to 6 and the substituent R^{10} is hydrogen or an alkyl, cycloalkyl, or alkoxy radical. No substituent contains more than 12 carbon atoms. The total number of carbon atoms in the substituent does

20 not exceed 12 per lactone ring. Examples are hydroxycaproic acid, hydroxybutyric acid, hydroxydecanoic acid, and/or hydroxystearic acid.

- Preferred for the preparation of the polyester diols is
- 25 the unsubstituted ###-caprolactone, where m is 4 and all R^{10} substituents are hydrogen. The reaction with lactone is started by low molecular mass polyols such as ethylene glycol, 1,3-propanediol, 1,4-butanediol, or dimethylolcyclohexane. It is also possible, however, to

react other reaction components, such as ethylenediamine, alkylaldiolamines, or else urea, with caprolactone. Other suitable diols of relatively high molecular mass are polylactam diols, which are
5 prepared by reacting, for example, ###-caprolactam with low molecular mass diols.

Further examples of suitable polyols include polyether polyols, especially those having a number-average
10 molecular weight of from 400 to 5 000, in particular from 400 to 3 000. Examples of highly suitable polyether diols are polyether diols of the general formula $H-(O-(CHR^{11})_o-)_pOH$, where the substituent R^{11} is hydrogen or a lower, unsubstituted or substituted alkyl
15 radical, the index o is from 2 to 6, preferably from 3 to 4, and the index p is from 2 to 100, preferably from 5 to 50. Especially suitable examples are linear or branched polyether diols such as poly(oxyethylene) glycols, poly(oxypropylene) glycols, and
20 poly(oxybutylene) glycols.

The polyether diols ought on the one hand not to introduce excessive amounts of ether groups, since otherwise the polyurethanes (A) for inventive use that
25 are formed start to swell in water. On the other hand, they can be used in amounts which ensures the nonionic stabilization of the polyurethanes (A). In that case they serve as the functional nonionic groups (a3) described below.

The polyurethane (A) for inventive use comprises alternatively

5 (a1) functional groups convertible into cations by neutralizing agents and/or quaternizing agents, and/or cationic groups, especially ammonium groups,

10 or

(a2) functional groups convertible into anions by neutralizing agents, and/or anionic groups, especially carboxylic acid and/or carboxylate groups,

15

and/or

(a3) nonionic hydrophilic groups, especially
20 poly(alkylene ether) groups.

Examples of suitable functional groups (a1) for inventive use and convertible into cations by neutralizing agents (D) and/or quaternizing agents are
25 primary, secondary or tertiary amino groups, secondary sulfide groups or tertiary phosphine groups, especially tertiary amino groups or secondary sulfide groups.

Examples of suitable cationic groups (a1) for inventive use are primary, secondary, tertiary or quaternary ammonium groups, tertiary sulfonium groups or quaternary phosphonium groups, preferably quaternary ammonium groups or quaternary ammonium groups, tertiary sulfonium groups, but especially tertiary sulfonium groups.

10 Examples of suitable functional groups (a2) for inventive use and convertible into anions by neutralizing agents (D) are carboxylic acid, sulfonic acid or phosphonic acid groups, especially carboxylic acid groups.

15 Examples of suitable anionic groups (a2) for inventive use are carboxylate, sulfonate or phosphonate groups, especially carboxylate groups.

20 Examples of suitable neutralizing agents (D) for functional groups (a1) convertible into cations are organic and inorganic acids such as formic acid, acetic acid, lactic acid, dimethylolpropionic acid, citric acid, sulfuric acid, hydrochloric acid or phosphoric acid.

25

Examples of suitable neutralizing agents (D) for functional groups (a2) convertible into anions are tertiary amines, such as trimethylamine, triethylamine, tributylamine, dimethylaniline, diethylaniline,

triphenylamine, dimethylethanolamine, diethylethanol-
amine, methyldiethanolamine or triethanolamine, for
example. Neutralization may take place in organic phase
or in aqueous phase. A preferred neutralizing agent
5 used is dimethylethanolamine.

The total amount of neutralizing agent (D) used in the
aqueous basecoat material of the invention is chosen so
that from 1 to 100 equivalents, preferably from 50 to
10 90 equivalents, of the functional groups (a1) or (a2)
of the polyurethane (A) for inventive use are
neutralized.

Of these functional (potentially) ionic groups (a1) and
15 (a2) and functional nonionic groups (a3), the
(potentially) anionic groups (a2) are advantageous and
are therefore used with particular preference.

The introduction of (potentially) anionic groups (a2)
20 into the polyurethane molecules takes place by way of
the incorporation of compounds which contain in the
molecule at least one isocyanate-reactive group and at
least one group capable of forming anions; the amount
to be used may be calculated from the target acid
25 number.

Examples of suitable compounds of this kind are those
containing two isocyanate-reactive groups in the
molecule. Suitable isocyanate-reactive groups are, in

- particular, hydroxyl groups, and also primary and/or secondary amino groups. Accordingly it is possible, for example, to use alkanolic acids having two substituents on the ###-positioned carbon atom. The substituent may
- 5 be a hydroxyl group, an alkyl group, or, preferably, an alkylol group. These alkanolic acids have at least one, generally from 1 to 3, carboxyl groups in the molecule. They have 2 to about 25, preferably 3 to 10, carbon atoms. Examples of suitable alkanolic acids are
- 10 dihydroxypropionic acid, dihydroxysuccinic acid, and dihydroxybenzoic acid. A particularly preferred group of alkanolic acids are the ###,###-dimethylolalkanoic acids of the general formula $R^{12}-C(CH_2OH)_2COOH$, R^{12} being a hydrogen atom or an alkyl group having up to about 20
- 15 carbon atoms. Examples of especially suitable alkanolic acids are 2,2-dimethylolacetic acid, 2,2-dimethylolpropionic acid, 2,2-dimethylolbutyric acid, and 2,2-dimethylolpentanoic acid. The preferred dihydroxyalkanoic acid is 2,2-dimethylolpropionic acid.
- 20 Examples of compounds containing amino groups are ###,###-diaminovaleric acid, 3,4-diaminobenzoic acid, 2,4-diaminotoluenesulfonic acid, and 2,4-diaminodiphenyl ether sulfonic acid.
- 25 Stabilizing nonionic poly(oxyalkylene) groups (a3) may be introduced as lateral or terminal groups into the polyurethane molecules. For this purpose it is possible to use, for example, alkoxy poly(oxyalkylene) alcohols having the general formula $R^{13}O-(CH_2-CHR^{14}-O)_nH$, where

R¹³ is an alkyl radical having 1 to 6 carbon atoms, R¹⁴ is a hydrogen atom or an alkyl radical having 1 to 6 carbon atoms, and the index r is a number between 20 and 75. (cf. the patents EP-A-0 354 261 or
5 EP-A-0 424 705).

The use of polyols, polyamines and amino alcohols leads to an increase in the molecular weight of the polyurethanes (A).

10

Suitable polyols for the chain extension are polyols containing up to 36 carbon atoms per molecule, such as ethylene glycol, diethylene glycol, triethylene glycol, 1,2-propanediol, 1,3-propanediol, 1,4-butanediol, 1,2-
15 butylene glycol, 1,6-hexanediol, trimethylolpropane, castor oil or hydrogenated castor oil, di-trimethylolpropane ether, pentaerythritol, 1,2-cyclohexanediol, 1,4-cyclohexanedimethanol, bisphenol A, bisphenol F, neopentyl glycol, neopentyl glycol
20 hydroxypivalate, hydroxyethylated or hydroxypropylated bisphenol A, hydrogenated bisphenol A or mixtures thereof (cf. patents EP-A-0 339 433, EP-A-0 436 941, EP-A-0 517 707).

25 Examples of suitable polyamines have at least two primary and/or secondary amino groups. Polyamines are essentially alkylene polyamines having 1 to 40 carbon atoms, preferably about 2 to 15 carbon atoms. They may carry substituents which have no hydrogen atoms that

are reactive with isocyanate groups. Examples are polyamines having a linear or branched aliphatic, cycloaliphatic or aromatic structure and at least two primary amino groups.

5

Diamines include hydrazine, ethylenediamine, propylenediamine, 1,4-butylenediamine, piperazine, 1,4-cyclohexyldimethylamine, 1,6-hexamethylenediamine, trimethylhexamethylenediamine, methanediamine, isophoronediamine, 4,4'-diaminodicyclohexylmethane, and aminoethylenethanolamine. Preferred diamines are hydrazine, alkyl- or cycloalkyldiamines such as propylenediamine and 1-amino-3-aminomethyl-3,5,5-trimethylcyclohexane.

15

It is also possible to use polyamines containing more than two amino groups in the molecule. In these cases, however, it should be ensured - for example, by using monoamines as well - that no crosslinked polyurethane resins are obtained. Polyamines of this kind which may be used are diethylenetriamine, triethylenetetramine, dipropylenediamine, and dibutylenetriamine. An example of a monoamine is ethylhexylamine (cf. the patent EP-A-0 089 497).

25

Examples of suitable amino alcohols are ethanolamine or diethanolamine.

In the aqueous basecoat materials of the invention, the polyurethanes (A) are present advantageously in an amount of from 1.0 to 50%, preferably from 2.0 to 40%, with particular preference from 3.0 to 30%, with very particular preference from 4.0 to 25%, and in particular from 5.0 to 20% by weight, based in each case on the overall weight of the respective aqueous basecoat material of the invention.


- 10 The further essential constituent of the coating material of the invention is at least one crosslinking agent (B).

- Examples of suitable crosslinking agents (B) are amino resins, compounds or resins containing anhydride groups, compounds or resins containing epoxide groups, tris(alkoxycarbonylamino)triazines, compounds or resins containing carbonate groups, blocked and/or nonblocked polyisocyanates, beta-hydroxyalkylamides, and compounds containing on average at least two groups capable of transesterification, examples being reaction products of malonic diesters and polyisocyanates or of esters and partial esters of polyhydric alcohols of malonic acid with monoisocyanates, as described by the European patent EP-A-0 596 460.

Crosslinking agents of this kind are well known to the skilled worker and are offered by numerous companies as sales products.

Examples of suitable polyepoxides are, in particular, all known aliphatic and/or cycloaliphatic and/or aromatic polyepoxides, based for example on bisphenol A or bisphenol F. Examples of suitable polyepoxides also include the polyepoxides available commercially under the designations Epikote® from Shell, Denacol® from Nagase Chemicals Ltd., Japan, such as, for example, Denacol EX-411 (pentaerythritol polyglycidyl ether), Denacol EX-321 (trimethylolpropane polyglycidyl ether), Denacol® EX-512 (polyglycerol polyglycidyl ether) and Denacol® EX-521 (polyglycerol polyglycidyl ether).

The suitable tris(alkoxycarbonylamino)triazines had the following formula:



Examples of suitable tris(alkoxycarbonylamino)triazines are described in the patents US-A-4,939,213, US-A-5,084,541 or EP-A-0 624 577. Use is made in particular of the tris(methoxy-, tris(butoxy- and/or tris(2-ethylhexoxycarbonylamino)triazines.

Of advantage are the methyl butyl mixed esters, the butyl 2-ethylhexyl mixed esters and the butyl esters. These have the advantage over the straight methyl ester
5 of better solubility in polymer melts, and also have less of a tendency to crystallize.

An example of a suitable polyanhydride is polysuccinic anhydride.

10

Examples of suitable beta-hydroxyalkylamides are N,N,N',N'-tetrakis(2-hydroxyethyl)adipamide or N,N,N',N'-tetrakis(2-hydroxypropyl)adipamide.

15 Further examples of suitable crosslinking agents are the blocked polyisocyanates.

Examples of suitable blocking agents are the blocking agents known from the US patent US-A-4,444,954:

20

i) phenols such as phenol, cresol, xyleneol, nitrophenol, chlorophenol, ethylphenol, t-butylphenol, hydroxybenzoic acid, esters of this acid or 2,5-di-tert-butyl-4-
25 hydroxytoluene;

ii) lactams, such as ϵ -caprolactam, δ -valerolactam, γ -butyrolactam or β -propiolactam;

- iii) active methylenic compounds, such as diethyl malonate, dimethyl malonate, ethyl or methyl acetoacetate or acetylacetone;
- 5 iv) alcohols such as methanol, ethanol, n-propanol, isopropanol, n-butanol, isobutanol, t-butanol, n-amyl alcohol, t-amyl alcohol, lauryl alcohol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol monobutyl ether, diethylene glycol monomethyl ether, diethylene glycol monoethyl ether, propylene glycol monomethyl ether, methoxymethanol, glycolic acid, glycolic esters, lactic acid, lactic esters,
- 10 methanololurea, methylolmelamine, diacetone alcohol, ethylenechlorohydrin, ethylenebromohydrin, 1,3-dichloro-2-propanol, 1,4-cyclohexyldimethanol or acetocyanohydrin;
- 15
- 20 v) mercaptans such as butyl mercaptan, hexyl mercaptan, t-butyl mercaptan, t-dodecyl mercaptan, 2-mercaptobenzothiazole, thiophenol, methylthiophenol or ethylthiophenol;
- 25 vi) amides such as acetoanilide, acetoanisidinamide, acrylamide, methacrylamide, acetamide, stearamide or benzamide;

- vii) imides such as succinimide, phthalimide or maleimide;
- 5 viii) amines such as diphenylamine, phenylnaphthylamine, xylylidine, N-phenylxylylidine, carbazole, aniline, naphthylamine, butylamine, dibutylamine or butylphenylamine;
- 10 ix) imidazoles such as imidazole or 2-ethylimidazole;
- x) ureas such as urea, thiourea, ethyleneurea, ethylenethiourea or 1,3-diphenylurea;
- 15 xi) carbamates such as phenyl N-phenylcarbamate or 2-oxazolidone;
- xii) imines such as ethyleneimine;
- 20 xiii) oximes such as acetone oxime, formaldoxime, acetaldoxime, acetoxime, methyl ethyl ketoxime, diisobutyl ketoxime, diacetyl monoxime, benzophenone oxime or chlorohexanone oximes;
- 25 xiv) salts of sulfurous acid such as sodium bisulfite or potassium bisulfite;

xv) hydroxamic esters such as benzyl methacrylohydroxamate (BMH) or allyl methacrylohydroxamate; or

5 xvi) substituted pyrazoles, ketoximes, imidazoles or triazoles; and also

xvii) mixtures of these blocking agents, especially dimethylpyrazole and triazoles, malonates and
10 acetoacetates or dimethylpyrazole and succinimide.

Examples of suitable organic polyisocyanates for blocking are in particular the polyisocyanates known as
15 paint polyisocyanates, containing aliphatically, cycloaliphatically, araliphatically and/or aromatically bonded isocyanate groups. Preference is given to polyisocyanates containing from 2 to 5 isocyanate groups per molecule and having viscosities of from 100
20 to 10 000, preferably from 100 to 5 000. Furthermore, the polyisocyanates can have been hydrophilically or hydrophobically modified in a customary and known way.

Further examples of suitable polyisocyanates for
25 blocking are described in "Methoden der organischen Chemie", Houben-Weyl, Volume 14/2, 4th edition, Georg Thieme Verlag, Stuttgart 1963, page 61 to 70, and by W. Siefken, Liebigs Annalen der Chemie, Volume 562, pages 75 to 136. Suitable examples include the

polyurethane prepolymers containing isocyanate groups, which can be prepared by reacting polyols with an excess of polyisocyanates and which are preferably of low viscosity.

5

Further examples of suitable polyisocyanates for blocking are polyisocyanates containing isocyanurate, biuret, allophanate, iminooxadiazinedione, urethane, urea and/or uretdione groups. Polyisocyanates
10 containing urethane groups, for example, are obtained by reacting some of the isocyanate groups with polyols, such as trimethylolpropane and glycerol, for example. It is preferred to use aliphatic or cycloaliphatic polyisocyanates, especially hexamethylene diisocyanate,
15 dimerized and trimerized hexamethylene diisocyanate, isophorone diisocyanate, dicyclohexylmethane 2,4'-diisocyanate, dicyclohexylmethane 4,4'-diisocyanate, diisocyanates derived from dimeric fatty acids, as marketed under the commercial designation DDI 1410 by
20 the company Henkel and described in the patents DO 97/49745 and WO 97/49747, especially 2-heptyl-3,4-bis(9-isocyanatononyl)-1-pentylcyclohexane; or 1,2-, 1,4- or 1,3-bis(isocyanatomethyl)cyclohexane, 1,2-, 1,4- or 1,3-bis(2-isocyanatoethyl)cyclohexane, 1,3-
25 bis(3-isocyanatoprop-1-yl)cyclohexane or 1,2-, 1,4- or 1,3-bis(4-isocyanatobut-1-yl)cyclohexane, 1,8-diisocyanato-4-isocyanatomethyloctane, 1,7-diisocyanato-4-isocyanatomethylheptane or 1-isocyanato-2-(3-iso-

cyanatopropyl)cyclohexane, or mixtures of these polyisocyanates.

Very particular preference is given to using mixtures
5 of polyisocyanurates which contain uretdione and/or
isocyanurate groups and/or allophanate groups that are
based on hexamethylene diisocyanate, as formed by
catalytic oligomerization of hexamethylene diisocyanate
using appropriate catalysts.

10

In particular it is possible to use amino resins,
examples being melamine resins, guanamine resins or
urea resins, as crosslinking agents (B). In this case
it is possible to use any amino resin which is suitable
15 for transparent topcoat materials or clearcoat
materials, or a mixture of such amino resins. For
further details refer to Römpp Lexikon Lacke und
Druckfarben, Georg Thieme Verlag, 1998, page 29, "Amino
resins", and the textbook "Lackadditive" by Johan
20 Bieleman, Wiley-VCH, Weinheim, New York, 1998, pages
242 ff., or to the book "Paints, Coatings and
Solvents", second completely revised edition, Editors
D. Stoye and W. Freitag, Wiley-VCH, Weinheim, New York,
1998, pages 80 ff. Also suitable are the customary and
25 known amino resins some of whose methylol and/or
methoxymethyl groups have been defunctionalized by
means of carbamate or allophanate groups. Crosslinking
agents of this kind are described in patents
US-A-4 710 542 and EP-B-0 245 700 and also in the

article by B. Singh and coworkers, "Carbamylmethylated Melamines, Novel Crosslinkers for the Coatings Industry" in Advanced Organic Coatings Science and Technology Series, 1991, Volume 13, pages 193 to 207.

5

Preferably, the amino resins are contained in the aqueous basecoat materials of the invention as the predominant or sole crosslinking agents (B). The other abovementioned crosslinking agents (B) can be used as

10 additional crosslinking agents (B) for the further advantageous variation of the profile of properties of the aqueous basecoat materials of the invention and of the inventive basecoats and inventive multicoat color and/or effect paint systems produced from them, their
15 proportion among the crosslinking agents (B) in that case being < 50% by weight.

In the aqueous basecoat materials of the invention, the crosslinking agents (B) are employed preferably in an
20 amount of from 0.1 to 30%, more preferably from 0.3 to 20%, with particular preference from 0.5 to 10%, and in particular from 1.0 to 8.0% by weight, based in each case on the overall weight of the respective aqueous basecoat material of the invention.

25

Yet another essential constituent of the aqueous basecoat material of the invention is at least one color and/or effect pigment (C). The pigments (C) can be composed of organic or inorganic compounds. The

aqueous basecoat material of the invention therefore ensures, owing to this large number of suitable pigments, a universal breadth of use, and permits the realization of a large number of color shades and optical effects.

As effect pigments (C) it is possible to use metal flake pigments such as commercial aluminum bronzes, aluminum bronzes chromated as per DE-A-36 36 183, commercial stainless steel bronzes, and nonmetallic effect pigments, such as pearlescent pigments and interference pigments, for example. For further details refer to Römpp Lexikon Lacke und Druckfarben, Georg Thieme Verlag, 1998, pages 176, "Effect pigments" and pages 380 and 381, "Metal oxide/mica pigments" to "Metal pigments".

Examples of suitable inorganic color pigments (C) are titanium dioxide, iron oxides, Sicotrans yellow, and carbon black. Examples of suitable organic color pigments (C) are thioindigo pigments indanthrene blue, Cromophthal red, Irgazine orange and Heliogen green. For further details refer to Römpp Lexikon Lacke und Druckfarben, Georg Thieme Verlag, 1998, pages 180 and 181, "Iron blue pigments" to "Black iron oxide", pages 451 to 453, "Pigments" to "Pigment volume concentration", page 563 "Thioindigo pigments" and page 567 "Titanium dioxide pigments".

The fraction of the pigments (C) in the aqueous basecoat material of the invention can vary extremely widely and is guided primarily by the opacity of the pigments (C), by the desired shade and by the desired optical effect. In the aqueous basecoat material of the invention, the pigments (C) are present in an amount of preferably from 0.5 to 50%, more preferably from 0.5 to 45%, with particular preference from 0.5 to 40%, with very particular preference from 0.5 to 35%, and in particular from 0.5 to 30% by weight, based in each case on the overall weight of the aqueous basecoat material of the invention. The pigment/binder ratio, i.e., the ratio of the pigments (C) to the above-described polyurethanes (A) or to the polyurethanes (A) and the hereinbelow-described polyacrylate resins (H) and polyesters (I), can also vary extremely widely. This ratio is preferably from 4.0:1.0 to 1.0:50, more preferably from 3.5:1.0 to 1.0:50, with particular preference from 3.0:1.0 to 1.0:40, with very particular preference from 2.5:1.0 to 1.0:30, and in particular from 2.3:1.0 to 1.0:25.

These pigments (C) may also be incorporated into the aqueous basecoat materials of the invention by way of pigment pastes, in which case suitable dispersing resins include the above-described polyurethanes (A) and/or the hereinbelow-described polyacrylate resins (H) and/or polyester resins (I).

Yet another essential constituent of the aqueous basecoat material of the invention is at least one inorganic thickener (E).

- 5 Examples of suitable inorganic thickeners (E) are inorganic phyllosilicates, preferably smectites, especially montmorillonites and hectorites, such as aluminum magnesium silicates, sodium magnesium and sodium magnesium fluorine lithium phyllosilicates of
10 the montmorillonite type or inorganic phyllosilicates such as aluminum magnesium silicates, aluminum magnesium silicates, sodium magnesium and sodium magnesium fluorine lithium phyllosilicates of the montmorillonite type. For further details, refer to the
15 book by Johan Bielemann "Lackadditive", Wiley-VCH, Weinheim, New York, 1998, pages 17 to 30.

In the aqueous basecoat materials of the invention, the thickeners (E) are present preferably in an amount of
20 from 0.01 to 5.0%, more preferably from 0.05 to 3.0%, with particular preference from 0.1 to 2.5%, with very particular preference from 0.2 to 2.0%, and in particular from 0.3 to 1.5% by weight, based in each case on the overall weight of the aqueous basecoat
25 material of the invention.

In one preferred embodiment of the aqueous basecoat material of the invention, it comprises in addition to the polyurethanes (A) at least one water-soluble or

-dispersible polyacrylate resin (H) prepared in the presence of a water-soluble or -dispersible polyurethane.

- 5 Examples of suitable polyurethanes in whose presence the polyacrylate resin (H) is prepared contain olefinically unsaturated groups which are lateral, terminal and/or located within the main polymer chain, or contain no olefinically unsaturated groups. Examples
10 of highly suitable polyurethanes of this kind are known from the patents EP-A-0 521 928, EP-A-0 522 420, EP-A-0 522 419 or EP-A-0 730 613 (olefinically unsaturated) or DE-A-44 37 535 (saturated). Examples of especially suitable polyurethanes are the above-
15 described polyurethanes (A), especially the polyurethanes (A) containing carboxylic acid groups and/or carboxylate groups.

Accordingly, the polyacrylate resins (H) which contain
20 carboxylic acid groups and/or carboxylate groups as solubilizing or dispersing groups are of advantage in accordance with the invention and are therefore used with preference. As regards the neutralization of the polyacrylate resins (H), the comments made above in
25 relation to the polyurethanes (A) apply analogously.

In accordance with the invention it is of advantage to prepare the polyacrylate resins (H) in the presence of

saturated polyurethanes (A), and so this variant is particularly preferred.

Very particularly highly suitable polyacrylate resins
5 (H) are obtained by copolymerizing the olefinically
unsaturated monomers (h) described below, of which at
least one contains at least one carboxylic acid group
and preferably at least one contains at least one
hydroxyl group and is substantially free from acid
10 groups.

Examples of suitable monomers (h) are:

Monomers (h1):

15 Hydroxyalkyl esters of acrylic acid, methacrylic acid
of another alpha,beta-ethylenically unsaturated
carboxylic acid which are derived from an alkylene
glycol which is esterified with the acid, or are
obtainable by reacting the acid with an alkylene oxide,
20 especially hydroxyalkyl esters of acrylic acid,
methacrylic acid or ethacrylic acid in which the
hydroxyalkyl group contains up to 20 carbon atoms, such
as 2-hydroxyethyl, 2-hydroxypropyl, 3-hydroxypropyl,
3-hydroxybutyl, 4-hydroxybutyl acrylate, methacrylate,
25 ethacrylate or crotonate; 1,4-bis(hydroxy-
methyl)cyclohexane, octahydro-4,7-methano-1H-indenedi-
methanol or methylpropanediol monoacrylate, mono-
methacrylate, monoethacrylate or monocrotonate; or
reaction products of cyclic esters, such as epsilon-

caprolactone, for example, and these hydroxyalkyl esters; or olefinically unsaturated alcohols such as allyl alcohol or polyols such as trimethylolpropane monoallyl or diallyl ether or pentaerythritol monoallyl, diallyl or triallyl ether. These monomers (h1) of higher functionality are generally used only in minor amounts. In the context of the present invention, minor amounts of higher-functional monomers here are amounts which do not result in the crosslinking or gelling of the polyacrylate resins. Thus, for example, the proportion of trimethylolpropane monoallyl ether may be from 2 to 10% by weight, based on the overall weight of the monomers (h1) to (h6) used to prepare the polyacrylate resin. In addition, however, it is also possible to add from 2 to 10% by weight, based on the overall weight of the monomers (h) used to prepare the polyacrylate resin, of trimethylolpropane monoallyl ether to the finished polyacrylate resin. Although the olefinically unsaturated polyols (h1) can be used as the sole monomers (h1), it is of advantage in accordance with the invention to use them in combination with further monomers (h1).

Monomers (h2):

(Meth)acrylic alkyl or cycloalkyl esters having up to 20 carbon atoms in the alkyl radical, especially methyl, ethyl, propyl, n-butyl, sec-butyl, tert-butyl, hexyl, ethylhexyl, stearyl and lauryl acrylate or methacrylate; cycloaliphatic (meth)acrylic esters,

especially cyclohexyl, isobornyl, dicyclopentadienyl, octahydro-4,7-methano-1H-indenemethanol or tert-butylcyclohexyl (meth)acrylate; (meth)acrylic oxaalkyl esters or oxacycloalkyl esters such as ethyltriglycol
5 (meth)acrylate and methoxyoligoglycol (meth)acrylate having a molecular weight Mn of preferably 550; or other ethoxylated and/or propoxylated hydroxyl-free (meth)acrylic acid derivatives. These may include, in minor amounts, higher-functional (meth)acrylic alkyl or
10 cycloalkyl esters such as ethylene glycol, propylene glycol, diethylene glycol, dipropylene glycol, butylene glycol, 1,5-pentanediol, 1,6-hexanediol, octahydro-4,7-methano-1H-indenedimethanol or cyclohexane-1,2-, -1,3- or -1,4-diol di(meth)acrylate; trimethylolpropane di-
15 or tri(meth)acrylate; or pentaerythritol di-, tri- or tetra(meth)acrylate. In the context of the present invention, minor amounts of higher-functional monomers (h2) here are amounts which do not cause crosslinking or gelling of the polyacrylate resins.

20

Monomers (h3):

Ethylenically unsaturated monomers which carry at least one acid group, preferably a carboxyl group, per molecule, or a mixture of such monomers. As component
25 (h3) it is particularly preferred to use acrylic acid and/or methacrylic acid. It is also possible, however, to use other ethylenically unsaturated carboxylic acids having up to 6 carbon atoms in the molecule. Examples of such acids are ethacrylic acid, crotonic acid,

maleic acid, fumaric acid, and itaconic acid. It is also possible to use ethylenically unsaturated sulfonic or phosphonic acids, and/or their partial esters, as component (h3). Further suitable monomers (h3) include

5 mono(meth)acryloyloxyethyl maleate, succinate, and phthalate.

Monomers (h4):

Vinyl esters of alpha-branched monocarboxylic acids

10 having 5 to 18 carbon atoms in the molecule. The branched monocarboxylic acids may be obtained by reacting formic acid or carbon monoxide and water with olefins in the presence of a liquid, strongly acidic catalyst; the olefins may be cracking products from

15 paraffinic hydrocarbons, such as mineral oil fractions, and may contain both branched and straight-chain acyclic and/or cycloaliphatic olefins. In the reaction of such olefins with formic acid and/or with carbon monoxide and water, a mixture of carboxylic acids is

20 formed in which the carboxyl groups are located predominantly on a quaternary carbon atom. Other olefinic starting materials are, for example, propylene trimer, propylene tetramer, and diisobutylene. Alternatively, the vinyl esters may be prepared in a

25 conventional manner from the acids; for example, by reacting the acid with acetylene. Particular preference - owing to their ready availability - is given to the use of vinyl esters of saturated aliphatic

monocarboxylic acids having 9 to 11 carbon atoms and being branched on the alpha carbon atom.

Monomers (h5):

- 5 Reaction product of acrylic acid and/or methacrylic acid with the glycidyl ester of an alpha-branched monocarboxylic acid having 5 to 18 carbon atoms per molecule. The reaction of the acrylic or methacrylic acid with the glycidyl ester of a carboxylic acid
- 10 having a tertiary alpha carbon atom may take place before, during or after the polymerization reaction. As component (h5) it is preferred to use the reaction product of acrylic and/or methacrylic acid with the glycidyl ester of Versatic® acid. This glycidyl ester
- 15 is obtainable commercially under the name Cardura® E10. For further details, refer to Römpp Lexikon Lacke und Druckfarben, Georg Thieme Verlag, Stuttgart, New York, 1998, pages 605 and 606.

20 Monomers (h6):

Ethylenically unsaturated monomers substantially free from acid groups, such as

- olefins such as ethylene, propylene, 1-butene, 1-pentene, 1-hexene, cyclohexene, cyclopentene,
- 25 norbornene, butadiene, isoprene, cyclopentadiene and/or dicyclopentadiene;
- (meth)acrylamides such as (meth)acrylamide, N-methyl-, N,N-dimethyl-, N-ethyl-, N,N-diethyl-, N-propyl-, N,N-dipropyl, N-butyl-, N,N-dibutyl-,

N-cyclohexyl- and/or N,N-cyclohexyl-methyl-
(meth)acrylamide;

- monomers containing epoxide groups, such as the glycidyl ester of acrylic acid, methacrylic acid, 5 ethacrylic acid, crotonic acid, maleic acid, fumaric acid and/or itaconic acid;

- vinylaromatic hydrocarbons, such as styrene, alpha-alkylstyrenes, especially alpha-methylstyrene, arylstyrenes, especially diphenyl-10 ethylene, and/or vinyltoluene;

- nitriles such as acrylonitrile and/or methacrylonitrile;

- vinyl compounds such as vinyl chloride, vinyl fluoride, vinylidene dichloride, vinylidene difluoride; N-vinylpyrrolidone; vinyl ethers such as ethyl vinyl ether, n-propyl vinyl ether, isopropyl vinyl ether, n-butyl vinyl ether, isobutyl vinyl ether and/or vinyl cyclohexyl

- ether; vinyl esters such as vinyl acetate, vinyl propionate, vinyl butyrate, vinyl pivalate, vinyl esters of Versatic® acids, which are marketed under the brand name VeoVa® by the company Deutsche Shell Chemie (for further details, refer to Römpf Lexikon Lacke und Druckfarben, Georg Thieme Verlag, Stuttgart, New York, 1998, page 598 and also pages 605 and 606), and/or the vinyl ester of 2-methyl-2-ethylheptanoic acid; and/or

- polysiloxane macromonomers having a number-average molecular weight M_n of from 1 000 to 40 000,

preferably from 2 000 to 20 000, with particular preference from 2 500 to 10 000, and in particular from 3 000 to 7 000, and having on average from 0.5 to 2.5, preferably from 0.5 to 1.5, ethylenically unsaturated double bonds per molecule, as are described in DE-A-38 07 571 on pages 5 to 7, in DE-A-37 06 095 in columns 3 to 7, in EP-B-0 358 153 on pages 3 to 6, in US-A-4,754,014 in columns 5 to 9, in DE-A-44 21 823, or in the international patent application WO 92/22615 on page 12, line 18 to page 18, line 10, or acryloxysilane-containing vinyl monomers, preparable by reacting hydroxy-functional silanes with epichlorohydrin and then reacting the reaction product with methacrylic acid and/or hydroxyalkyl esters of (meth)acrylic acid.

In accordance with the invention it is especially advantageous to select the monomers (h) so as to give hydroxyl-containing polyacrylate resins which have an OH number of preferably from 0 to 200, more preferably from 60 to 140, acid numbers of preferably from 20 to 100, more preferably from 25 to 50, glass transition temperatures T_g of preferably from -25 to +80°C, more preferably from -20 to +40°C, and number-average molecular weights of preferably from 1 500 to 30 000, more preferably from 1 500 to 20 000 (determined by gel

permeation chromatography using polystyrene as internal standard).

The glass transition temperature T_g of the polyacrylate resins (H) is determined by the nature and amount of the monomers (h1) and, where appropriate (h2), (h3), (h4), (h5) and/or (h6) that are used. The skilled worker is able to select the monomers with the assistance of the following formula of Fox, which can be used for approximate calculation of the glass transition temperatures T_g of (co)polymers, especially polyacrylate resins:

$$\frac{1}{T_g} = \frac{1}{T_g} = \sum_{n=1}^x \frac{W_n}{T_{g_n}}; \quad \sum_{n=1}^x W_n = 1$$

T_g = glass transition temperature of the polyacrylate resin

W_n = weight fraction of the nth monomer

T_{g_n} = glass transition temperature of the homopolymer of the nth monomer

x = number of different monomers

Viewed in terms of its method, the preparation of the hydroxyl-containing polyacrylate resins (H) for inventive use has no special features but instead takes place in accordance with the customary and known

methods of radical polymerization in the presence of at least one polymerization initiator.

Examples of suitable polymerization initiators are
5 initiators which form free radicals, such as tert-butylperoxyethyl hexanoate, benzoyl peroxide, di-tert-amyl peroxide, azobisisobutyronitrile, and tert-butylperbenzoate. The initiators are used preferably in an amount of from 1 to 25% by weight, with particular
10 preference from 2 to 10% by weight, based on the overall weight of the monomers.

The polymerization is appropriately conducted at a temperature of from 80 to 200°C, preferably from 110 to
15 180°C.

It is preferred to commence the initiator feed a certain time, generally from about 1 to 15 minutes, before the monomers feed. Preference is also given to a
20 process wherein the addition of initiator is commenced at the same time as the addition of the monomers and ended about half an hour after the addition of the monomers has been ended. The initiator is preferably added in a constant amount per unit time. After the end
25 of the addition of initiator, the reaction mixture is held at polymerization temperature until (generally 1.5 hours) all of the monomers used have undergone substantially complete reaction. "Substantially complete reaction" is intended to denote that,

preferably, 100% by weight of the monomers used have been converted but that it is also possible for a small residual monomer content of not more than up to about 0.5% by weight, based on the weight of the reaction mixture, to remain unreacted.

One particularly preferred process for the preparation of the polyacrylate resins (H) is described in DE-A-44 37 535.

10

In this process, in a first step, a polyurethane free from copolymerizable double bonds, especially a polyurethane (A), is introduced in organic solution, after which a mixture of at least one monomer (h1) and at least one monomer (h2) and also, where appropriate, in each case at least one monomer (h4), (h5) and/or (h6) is added, and the mixture is copolymerized. After these monomers (h) have undergone almost complete conversion, in a second process step a mixture of at least one monomer (h3) and also in each case at least one monomer (h1) (h2), (h4), (h5) and/or (h6) is added, after which the resulting reaction mixture is polymerized to completion.

25 In terms of apparatus as well, the preparation of the polyacrylate resins (H) for inventive use has no special features as far as its method is concerned but instead takes place with the aid of the methods, customary and known in the polymers field, of

continuous or batchwise copolymerization under atmospheric or superatmospheric pressure in stirred tanks, autoclaves, tube reactors or Taylor reactors.

5 Examples of suitable copolymerization processes and apparatus are described in the patents DE-A-197 09 465, DE-C-197 09 476, DE-A-28 48 906, DE-A-195 24 182, EP-A-0 554 783, WO 95/27742 or WO 82/02387.

10 Following their preparation, the polyacrylate resins (H) are neutralized with at least one of the above-described suitable neutralizing agents (D), and dispersed in water. The total amount of neutralizing agent (D) used in the aqueous basecoat material of the
15 invention is chosen such that from 1 to 100 equivalents, preferably from 50 to 90 equivalents, of the carboxyl groups of the polyurethanes (A) for inventive use and of the polyacrylate resins (H) are neutralized.

20

The fraction of the polyacrylate resins (H) in the aqueous basecoat materials of the invention can vary widely. It is preferably from 0.1 to 10%, more preferably from 0.5 to 8.0%, with particular preference
25 from 0.6 to 6.0%, with very particular preference from 0.8 to 6.0%, and in particular from 1.0 to 6.0% by weight, based in each case on the overall weight of the respective aqueous basecoat material of the invention.

In yet another preferred embodiment of the aqueous basecoat material of the invention, it comprises at least one water-soluble or -dispersible polyester resin (I).

5

Examples of suitable starting products for preparing the polyester resins (I) are the compounds described above in connection with the preparation of the polyester polyols.

10

Examples of suitable polyester resins (I) and their preparation from said starting products are described in detail in the patents DE-A-40 09 858 or DE-A-44 37 535.

15

The fraction of the polyester resins (I) in the aqueous basecoat materials of the invention can also vary widely. It is preferably from 0.5 to 12%, more preferably from 0.7 to 10%, with particular preference from 0.8 to 9.0%, with very particular preference from 1.0 to 8.0%, and in particular from 1.5 to 7.0% by weight, based in each case on the overall weight of the respective aqueous basecoat material of the invention.

25

In addition to the constituents described above, the aqueous basecoat material of the invention may comprise customary and known additives (J) in effective amounts.

Examples of suitable additives (J) are

- organic and inorganic fillers such as chalk, calcium sulfate, barium sulfate, silicates such as talc or kaolin, silicas, oxides such as aluminum hydroxide or magnesium hydroxide, or organic fillers such as textile fibers, cellulose fibers, polyethylene fibers or wood flour; for further details refer to Römpp Lexikon Lacke und Druckfarben, Georg Thieme Verlag, 1998, pages 250 ff., "Fillers";
- customary and known oligomeric and polymeric binders such as thermally curable, hydroxyl-containing, linear and/or branched and/or block, comb and/or random poly(meth)acrylates or acrylate copolymers, polyesters, alkyds, acrylated polyesters, polylactones, polycarbonates, polyethers, epoxy resin-amine adducts, (meth)acrylate diols, partially hydrolyzed polyvinyl esters, or polyureas;
- customary and known thermally curable reactive diluents such as positionally isomeric diethyloctanediols or hydroxyl-containing hyperbranched compounds or dendrimers;
- low-boiling and/or high-boiling organic solvents ("long solvents");
- UV absorbers;
- light stabilizers such as HALS compounds, benzotriazoles or oxalanilides;

- free-radical scavengers;
- thermolabile free-radical initiators such as organic peroxides, organic azo compounds or C-C-cleaving initiators such as dialkyl peroxides, 5 peroxocarboxylic acids, peroxodicarbonates, peroxide esters, hydroperoxides, ketone peroxides, azo dinitriles or benzpinacol silyl ethers;
- crosslinking catalysts such as dibutyltin dilaurate, lithium decanoate or zinc octoate, or 10 amine-blocked organic sulfonic acids;
- devolatilizers, such as diazadicycloundecane;
- slip additives;
- polymerization inhibitors;
- defoamers;
- 15 - emulsifiers, especially nonionic emulsifiers such as alkoxyated alkanols and polyols, phenols and alkylphenols or anionic emulsifiers such as alkali metal salts or ammonium salts of alkanecarboxylic acids, alkanesulfonic acids, and sulfo acids of 20 alkoxyated alkanols and polyols, phenols and alkylphenols;
- wetting agents such as siloxanes, fluorine compounds, carboxylic monoesters, phosphates, polyacrylic acids and their copolymers, or 25 polyurethanes;
- adhesion promoters such as tricyclodecanedimethanol;
- leveling agents;

- film-forming auxiliaries such as cellulose derivatives;
- transparent fillers based on silica, alumina, titanium dioxide or zirconium oxide; for further details refer to Römpp Lexikon Lacke und Druckfarben, Georg Thieme Verlag, Stuttgart, 1998, pages 250 to 252;
- other rheology control additives, such as those known from patents WO 94/22968, EP-A-0 276 501, EP-A-0 249 201 or WO 97/12945; crosslinked polymeric microparticles, as disclosed for example in EP-A-0 008 127; silicas such as Aerosils; or synthetic polymers containing ionic and/or associative groups such as polyvinyl alcohol, poly(meth)acrylamide, poly(meth)acrylic acid, polyvinylpyrrolidone, styrene-maleic anhydride or ethylene-maleic anhydride copolymers and their derivatives or hydrophobically modified polyacrylates; and/or
- flame retardants.

Further examples of suitable coatings additives are described in the textbook "Lackadditive" by Johan Bieleman, Wiley-VCH, Weinheim, New York, 1998.

The aqueous basecoat materials of the invention preferably have a solids content at spray viscosity of from 5.0 to 60%, more preferably from 5.0 to 50%, with particular preference from 10 to 45%, with very

particular preference from 13 to 40%, and in particular from 13 to 35% by weight, based in each case on the overall weight of the respective aqueous basecoat material of the invention.

5

The preparation of the aqueous basecoat material of the invention has no special features but instead takes place in a customary and known manner by mixing of the above-described constituents in appropriate mixing equipment such as stirred tanks, dissolvers or extruders in accordance with the techniques suitable for preparing the respective aqueous basecoat materials.

10

15 The aqueous basecoat material of the invention is used to produce the coatings of the invention, especially multicoat paint systems, on primed or unprimed substrates.

20 Suitable substrates are all surfaces for coating which are not damaged by curing of the coatings present thereon using heat. Suitable substrates comprise, for example, the moldings, films and fibers of the invention, metals, plastics, wood, ceramic, stone,
25 textile, fiber assemblies, leather, glass, glass fibers, glass wool and rock wool, mineral-bound and resin-bound building materials, such as plasterboard panels and cement slabs or roof shingles, and composites of these materials. The coating system of

the invention, accordingly, is also suitable for applications outside of automotive finishing, particularly automobile finishing. In such applications it is suitable particularly for the coating of furniture and for industrial coating, including coil coating, container coating, and the impregnation or coating of electrical components. In the context of industrial coatings it is suitable for coating virtually all parts for private or industrial use such as radiators, domestic appliances, small metal parts such as nuts and bolts, hubcaps, wheel rims, packaging, or electrical components such as motor windings or transformer windings.

15 In the case of electrically conductive substrates it is possible to use primers, which are prepared in a customary and known manner from electrocoat materials. Both anodic and cathodic electrocoat materials are suitable for this purpose, but especially cathodics.

20 With the multicoat paint system of the invention it is also possible to coat primed or unprimed plastics such as, for example, ABS, AMMA, ASA, CA, CAB, EP, UF, CF, MF, MPF, PF, PAN, PA, PE, HDPE, LDPE, LLDPE, UHMWPE, 25 PET, PMMA, PP, PS, SB, PUR, PVC, RF, SAN, PBT, PPE, POM, PUR-RIM, SMC, BMC, PP-EPDM and UP (abbreviations to DIN 7728T1). The plastics to be coated can of course also be polymer blends, modified plastics or fiber-reinforced plastics. It is also possible to employ the

plastics that are commonly used in vehicle construction, especially motor vehicle construction.

In the case of unfunctionalized and/or apolar substrate
5 surfaces, these may be subjected prior to coating in a known manner to a pretreatment, such as with a plasma or by flaming, or may be provided with a water-based primer.

10 The multicoat paint systems of the invention may be produced in a variety of ways.

A first preferred variant of the process of the invention comprises the following steps:

- 15 (I) preparing a basecoat film by applying the aqueous basecoat material of the invention to the substrate,
(II) drying the basecoat film,
(III) preparing a clearcoat film by applying a clearcoat
20 material to the basecoat film, and
(IV) jointly curing the basecoat film and the clearcoat film, to give the basecoat and the clearcoat (wet-on-wet technique).

25 This variant offers particular advantages especially in the context of the coating of plastics, and is therefore employed with particular preference in that utility.

A second preferred variant of the process of the invention comprises the following steps:

- (I) preparing a surfacer film by applying a surfacer to the substrate,
- 5 (II) curing the surfacer film, to give the surfacer coat,
- (III) preparing a basecoat film by applying the aqueous basecoat material of the invention to the surfacer coat,
- 10 (IV) drying the basecoat film,
- (V) preparing a clearcoat film by applying a clearcoat material to the basecoat film, and
- (VI) jointly curing the basecoat film and the clearcoat film, to give the basecoat and the clearcoat (wet-on-wet technique).
- 15

A third preferred variant of the process of the invention comprises the following steps:

- (I) preparing a surfacer film by applying a surfacer to the substrate,
- 20 (II) drying the surfacer film,
- (III) preparing a basecoat film by applying the aqueous basecoat material of the invention to the surfacer film,
- 25 (IV) drying the basecoat film,
- (V) preparing a clearcoat film by applying a clearcoat material to the basecoat film, and

(VI) jointly curing the surfacer film, the basecoat film and the clearcoat film, to give the basecoat and the clearcoat (extended wet-on-wet technique).

5 The two last-mentioned variants offer particular advantages especially in the context of the coating of automobile bodies and are therefore employed with very particular preference in that utility.

10 It is found here to be a further particular advantage of the aqueous basecoat material of the invention and of the process of the invention that all customary and known clearcoat materials can be combined with the aqueous basecoat film of the invention in the context
15 of the processes of the invention.

Examples of suitable known one-component (1K), two-component (2K) or multicomponent (3K, 4K) clearcoat materials are known from the patents DE-A-42 04 518,
20 US-A-5,474,811, US-A-5,356,669, US-A-5,605,965, WO 94/10211, WO 94/10212, WO 94/10213, EP-A-0 594 068, EP-A-0 594 071, EP-A-0 594 142, EP-A 0 604 992, WO 94/22969, EP-A-0 596 460 or WO 92/22615.

25 One-component (1K) clearcoat materials are known to contain hydroxyl-containing binders and crosslinking agents such as blocked polyisocyanates, tris-(alkoxycarbonylamino)triazines and/or amino resins. In another variant they include as binders polymers

containing pendant carbamate and/or allophanate groups and carbamate- and/or allophanate-modified amino resin crosslinking agents (cf. US-A-5,474,811, US-A-5,356,669, US-A-5,605,965, WO 94/10211, 5 WO 94/10212, WO 94/10213, EP-A-0 594 068, EP-A-0 594 071 or EP-A-0 594 142).

Two-component (2K) or multicomponent (3K, 4K) clearcoat materials include as essential constituents, as is 10 known, hydroxyl-containing binders and polyisocyanate crosslinking agents, which are stored separately until they are used.

Examples of suitable powder clearcoat materials are 15 known, for example, from the German patent DE-A-42 22 194 or from the BASF Lacke + Farbe AG product information bulletin "Pulverlacke", 1990.

Powder clearcoat materials include as essential 20 constituents, as is known, binders containing epoxide groups, and polycarboxylic acid crosslinking agents.

Examples of suitable powder slurry clearcoat materials are known, for example, from the US patent 25 US-A-4,268,542 and from the German patent applications DE-A-195 18 392.4 and DE-A-196 13 547, or are described in the German patent application DE-A-198 14 471.7, unpublished at the priority date of the present specification.

Powder slurry clearcoat materials, as is known, comprise powder clearcoat materials in dispersion in an aqueous medium.

5

UV-curable clearcoat materials are disclosed, for example, by the patents EP-A-0 540 884, EP-A-0 568 967 or US-A-4,675,234.

- 10 Furthermore, the clearcoats may additionally be coated further with at least one other clearcoat, an example being an organically modified ceramic layer, thereby making it possible to improve significantly the scratch resistance of the multicoat paint system of the
- 15 invention.

Accordingly, the multicoat paint systems of the invention can differ in their structure.

- 20 In a first preferred variant of the multicoat paint system of the invention, the following coats lie above one another in the stated order:

- (1) a surfacer coat which absorbs mechanical energy,
- 25 (2) the color and/or effect basecoat, and
- (3) a clearcoat.

In the second preferred variant of the multicoat paint system of the invention, the following coats lie above one another in the stated order:

5 (1) the color and/or effect basecoat, and

(2) a clearcoat. This preferred variant is used in particular in the coating of plastics.

10 The aqueous basecoat material of the invention may be applied by all customary application methods, such as spraying, knife-coating, brushing, flowcoating, dipping, impregnating, trickling, or rolling, for example. The substrates to be coated may itself be at rest, with the application equipment or unit being moved. Alternatively, the substrate to be coated, especially a coil, may be moved, with the application unit being at rest relative to the substrate or being moved appropriately.

20

Preference is given to the use of spray application methods, such as compressed-air spraying, airless spraying, high-speed rotation, electrostatic spray application (ESTA), alone or in conjunction with hot spray application such as hot-air spraying, for example. Application may be conducted at temperatures of max. 70 to 80°C, so that suitable application viscosities are achieved without the short-term thermal stress being accompanied by any change in or damage to

the aqueous basecoat material or its overspray, which may be intended for reprocessing. For instance, hot spraying may be configured such that the aqueous basecoat material is heated in the spray nozzle for only a very short time, or is heated just a short way upstream of the spray nozzle.

The spray booth used for the application may be operated, for example, with an optionally temperature-controllable circulation, which is operated with an appropriate absorption medium for the overspray, an example being the aqueous basecoat material itself.

In general, the surfacer film, basecoat film and clearcoat film are applied in a wet film thickness such that they cure to give coats having the coat thicknesses which are necessary and advantageous for their functions. In the case of the surfacer coat, this coat thickness is from 10 to 150, preferably from 15 to 120, with particular preference from 10 to 100, and in particular from 10 to 90 μm ; in the case of the basecoat it is from 5 to 50, preferably from 5 to 40, with particular preference from 5 to 30, and in particular from 10 to 25 μm ; and in the case of the clearcoats it is from 10 to 100, preferably from 15 to 80, with particular preference from 20 to 70, and in particular from 25 to 60 μm .

The surfacer film, basecoat film and clearcoat film are cured thermally.

Full curing may take place after a certain rest time.

- 5 Its duration may be from 30 s to 2 h, preferably from 1 min to 1 h, and in particular from 1 min to 45 min. The rest time serves, for example, for the coating films to flow and undergo devolatilization, or for the evaporation of volatile constituents such as solvents.
- 10 The rest time may be assisted and/or shortened by the application of elevated temperatures of up to 90°C and/or by a reduced atmospheric humidity < 10 g water/kg air, especially < 5 g water/kg air, provided this does not entail any damage or change to the
- 15 coating films, such as premature complete crosslinking, for instance.

The thermal curing has no special features in terms of its method but instead takes place in accordance with

20 the customary and known methods, such as heating in a convection oven or irradiation with IR lamps. This thermal curing may also take place in stages. Advantageously, thermal curing takes place at a temperature of from 50 to 100°C, with particular

25 preference from 80 to 100°C, and in particular from 90 to 100°C, for a time of from 1 min up to 2 h, with particular preference from 2 min up to 1 h, and in particular from 3 min to 30 min. If substrates of high heat resistance are used, thermal crosslinking may also

be conducted at temperatures above 100°C. In this case it is generally advisable not to exceed temperatures of 180°C, preferably 160°C, and in particular 155°C.

- 5 In the case of clearcoats, depending on the clearcoat material used, curing may also take place with actinic radiation or both thermally and with actinic radiation (dual cure). Suitable actinic radiation includes electromagnetic radiation such as near infrared light
- 10 (NIR), visible light, UV radiation or X-rays, and/or corpuscular radiation such as electron beams.

- The multicoat paint systems of the invention exhibit an outstanding profile of properties which is very well
- 15 balanced in terms of mechanics, optics, corrosion resistance, and adhesion. Thus the multicoat paint systems of the invention possess the high optical quality and intercoat adhesion required by the market and do not give rise to any problems such as deficient
- 20 surfacer-coat condensation resistance, cracking (mud-cracking) in the basecoats or leveling defects or surface structures in the clearcoats.

- In particular, the multicoat paint system of the
- 25 invention exhibit an outstanding metallic effect, an excellent D.O.I. (distinctiveness of the reflected image), and an outstanding surface smoothness. They are weathering-stable, resistant to chemicals and bird

droppings, are scratch resistant, and exhibits very good reflow behavior.

Not least, however, it proves to be a very special
5 advantage that the use of the aqueous basecoat materials of the invention in the production of the multicoat paint systems of the invention results in only barely visible optical defects, if any.

10 Accordingly, the substrates coated with them have particular advantages such as a prolonged service life, a better esthetic impression on the viewer, and improved technological usefulness, so making them particularly economically attractive.

15

Examples and comparative experiments

Preparation example 1

20 **The preparation of an aqueous polyurethane dispersion**
(A)

716.6 parts by weight of a condensation product
(number-average molecular weight: 1410) of 1.81 mol of
25 a polymeric fatty acid (dimer content at least 98% by weight, trimer content not more than 2.0% by weight, monomer content traces at most), 0.82 mol of isophthalic acid, 0.61 mol of hexanediol and 0.61 mol of neopentyl glycol, 61 parts by weight of

dimethylolpropionic acid, 10.6 parts by weight of neopentyl glycol, 365 parts by weight of methyl ethyl ketone and 308.3 parts by weight of m-tetramethylxylylidene diisocyanate were heated at 80
5 degrees Celsius under nitrogen and with stirring in a suitable reaction vessel. Reaction was continued to an isocyanate content of 1.1% by weight, based on the overall amount of reaction mixture. Subsequently 52.6 parts by weight of trimethylolpropane were added, after
10 which the resulting reaction mixture was stirred at 80 degrees Celsius until free isocyanate groups were no longer detectable. Thereafter, slowly, 33 parts by weight of dimethylethanolamine, 255 parts by weight of butyl glycol and, subsequently, 2153 parts by weight of
15 deionized water were stirred in. The methyl ethyl ketone was distilled off under reduced pressure. This gave a fine dispersion whose pH was adjusted to 7.4 using dimethylethanolamine and whose nonvolatiles fraction was adjusted to 31% by weight using deionized
20 water.

Preparation example 2

The preparation of an aqueous polyester resin solution 25 (I)

A reactor equipped with stirrer, thermometer and packed column was charged with 729 parts by weight of neopentyl glycol, 768 parts by weight of hexanediol,

462 parts by weight of hexahydrophthalic anhydride and 1710 parts by weight of a polymeric fatty acid (dimer content at least 98% by weight, trimer content not more than 2% by weight, monomer content traces at most), and
5 this initial charge was melted. The resulting melt was heated with stirring in such a way that the overhead column temperature did not exceed 100 degrees Celsius. Esterification was carried out at 220 degrees Celsius maximum until an acid number of 9 was reached. After
10 the mixture had cooled to 180 degrees Celsius, 768 parts by weight of trimellitic anhydride were added and esterification was continued until an acid number of 32 was reached. Thereafter, the reaction mixture was cooled to 120 degrees Celsius and diluted with 1392
15 parts by weight of butyl glycol. After it had cooled to 90 degrees Celsius, 158 parts by weight of dimethylethanolamine were stirred in slowly, followed by 1150 parts by weight of deionized water. The resulting polyester resin solution was adjusted to a pH
20 of 7.6 using dimethylethanolamine and to a nonvolatiles fraction of 60% by weight using deionized water.

Preparation example 3

25 The preparation of a polyacrylate resin (H)

500 parts by weight of a condensation product (number-average molecular weight: 1423) of 1.0 mol of a polymeric fatty acid (dimer content at least 98% by

weight, dimer content not more than 2.0% by weight, monomer content traces at most), 1.5 mol of isophthalic acid, 1.6 mol of neopentyl glycol and 1.7 mol of hexanediol, 31.2 parts by weight of neopentyl glycol, 185 parts by weight of methyl ethyl ketone, 201.7 parts by weight of m-tetramethylxylylidene diisocyanate and 0.7 part by weight of dibutyltin dilaurate were heated at 80 degrees Celsius under nitrogen and with stirring. The reaction was continued to an isocyanate content of 1.3% by weight, based on the overall amount of reaction mixture. Thereafter, 30 parts by weight of diethanolamine were added and the resulting reaction mixture was stirred at 80 degrees Celsius until isocyanate groups were no longer detectable. Subsequently, 466 parts by weight of butyl glycol were stirred in, after which the methyl ethyl ketone was distilled off under reduced pressure. The resulting polyurethane solution was then adjusted to a nonvolatiles fraction of 60% by weight using butyl glycol.

A steel vessel equipped with monomer feed, initiator feed, thermometer, oil heating and reflux condenser was charged with 28.44 parts by weight of butyl glycol and 24.24 parts by weight of the abovementioned polyurethane solution, and this initial charge was heated to 110 degrees Celsius. Then a solution of 5.1 parts by weight of t-butyl perethylhexanoate in 6.0 parts by weight of butyl glycol was added uniformly at

a rate such that the addition was over after 5.5 hours. The beginning of the addition of initiator was also accompanied by commencement of the addition of a mixture of 18.36 parts by weight of n-butyl methacrylate, 17 parts by weight of methyl methacrylate, 17 parts by weight of lauryl methacrylate, 17.34 parts by weight of hydroxypropyl acrylate and 12.75 parts by weight of styrene. The monomer mixture was added uniformly at a rate such that the addition was over in five hours. After all of the initiator solution had been added, the reaction mixture was held at 110 degrees Celsius for a further hour.

Subsequently, a solution of 1.17 parts by weight of t-butyl perethylhexanoate in 3.5 parts by weight of butyl glycol was added uniformly at a rate such that the addition was over after 1.5 hours. The beginning of the addition of the initiator solution was also accompanied by the commencement of addition of a mixture of 5.85 parts by weight of acrylic acid and 4.65 parts by weight of n-butyl methacrylate, 2.94 parts by weight of methyl methacrylate, 5.90 parts by weight of lauryl methacrylate, 1.25 parts by weight of hydroxypropyl acrylate and 2.94 parts by weight of styrene. The monomer mixture was added uniformly at a rate such that the addition was over within one hour. Thereafter, the temperature of the reaction mixture was held at 110 degrees Celsius for 1.5 hours more. The resulting resin solution was concentrated by

distillation under reduced pressure to a solids content of 80% by weight and at this temperature was neutralized with dimethylethanolamine over the course of 30 minutes to a degree of neutralization of 80%. The resin solution was cooled to 60 degrees Celsius, after which the heating was shut off. Then water was added slowly until the solids content of the dispersion was 40% by weight. The dispersion had an acid number of 36.7 mg KOH/g and a pH of 7.6.

Examples 1 and 2 and comparative experiments C1 and C2

The preparation of inventive (examples 1 and 2) and noninventive (comparative experiments C1 and C2)

aqueous basecoat materials

The preparations of the inventive aqueous basecoat materials of examples 1 and 2 and of the noninventive aqueous basecoat material of comparative experiment C2 were conducted in analogy to the preparation instructions indicated below for the noninventive aqueous basecoat material of comparative experiment C1. Table 1 gives an overview of the amounts of the starting products employed.

For comparative experiment C1, the thickener 1 (paste of a synthetic sodium magnesium phyllosilicate from Laporte; 3% in water) was introduced initially. Added to this with stirring were deionized water, thickener 3

- (3% aqueous solution of a polyacrylic acid from Allied Colloids; trade name: Viscalex), the polyurethane dispersion (A) from preparation example 1, the polyester resin solution (I) from preparation example
- 5 2, the solution of the polyacrylate (H) from preparation example 3, butyl glycol, a commercial melamine resin in butanol (Maprenal® VMF3924), a silica filler paste (12 parts by weight of Syloid® ED-3 from Grace; 30 parts by weight of the abovementioned
- 10 polyester resin solution (I)), a neutralizing agent (D) (dimethylethanolamine, 10% in water), a solution of a commercial defoamer based on alkynediol (50% in butyl glycol; from Air Products), deionized water, a pigment paste 1 (63 parts by weight of polyurethane dispersion,
- 15 31 parts by weight of titanium rutile Tayca® MT500HD from Tayca), a pigment paste 2 (64 parts by weight of polyurethane dispersion and 32 parts by weight of titanium dioxide UVL 530 from Kemira).
- 20 Prepared separately from this was an aluminum pigment slurry composed of 5.0 parts by weight of a commercial aluminum paste (Alu-Stapa-Hydrolux® 2192 from Eckart), 6.0 parts by weight of solvent and 2.4 parts by weight of the polyester resin solution (I). This aluminum
- 25 pigment slurry was stirred into the mixture described above.

The resultant mixture was then neutralized to a pH of about 8.0 using the neutralizing solution (D) and was

adjusted using deionized water to a viscosity of 65 mPas under a shear of 1291 s⁻¹.

For comparative experiment C2, comparative experiment
5 C1 was repeated but using the thickener 2 instead of the thickener 1. Said thickener 2 is a 3% solution of a synthetic sodium magnesium phyllosilicate from Südchemie.

10 For example 1, comparative experiment C1 was repeated but using the thickener 4 instead of the thickener 3. Said thickener 4 is a mixture of 50% by weight of a polyurethane-based associative thickener (G) (Nopco® DSX1550 from Henkel) and 50% by weight of butyl glycol.

15 For example 2, example 1 was repeated but using, instead of butyl glycol, dipropylene glycol monoalkyl ether for the preparation of the aluminum pigment slurry.

20 The aqueous basecoat materials of comparative experiment C2 and of examples 1 and 2 were also adjusted using neutralizing solution (D) to a pH of about 8.0 and using deionized water to a viscosity of
25 65 mPas under a shear of 1291 s⁻¹.

Table 1 gives an overview of the amounts of the starting products and of the composition of the aqueous basecoat materials.

Table 1: The composition of the inventive (examples 1 and 2) and of the noninventive (comparative experiments C1 and C2) aqueous basecoat materials

5

| Constituents | Comparative experiments: | | Examples: | |
|---------------------------------|--------------------------|------|-----------|------|
| | C1 | C2 | 1 | 2 |
| Thickener 1 | 29 | - | 29 | 29 |
| Thickener 2 | - | 29 | - | - |
| Deionized water | 9.0 | 9.0 | 9.0 | 9.0 |
| Thickener 3 | 5.5 | 5.5 | - | - |
| Polyurethane dispersion (A) | 21.5 | 21.5 | 21.5 | 21.5 |
| Polyester solution (I) | 2.0 | 2.0 | 2.0 | 2.0 |
| Polyacrylate resin solution (H) | 5.0 | 5.0 | 5.0 | 5.0 |
| Butyl glycol | 2.0 | 2.0 | 2.0 | 2.0 |
| Melamine resin (B) | 5.0 | 5.0 | 5.0 | 5.0 |
| Filler paste | 1.2 | 1.2 | 1.2 | 1.2 |
| Neutralizing agent (D) | 0.4 | 0.4 | 0.4 | 0.4 |
| Defoamer | 2.0 | 2.0 | 2.0 | 2.0 |
| Thickener 4 | - | - | 1.6 | 1.6 |
| Deionized water | 4.0 | 4.0 | 4.0 | 4.0 |
| Pigment paste 1 | 4.3 | 4.3 | 4.3 | 4.3 |
| Pigment paste 2 | 0.8 | 0.8 | 0.8 | 0.8 |
| Alu-Stapa-Hydrolux® | 5.0 | 5.0 | 5.0 | 5.0 |
| Butyl glycol | 6.0 | 6.0 | 6.0 | - |
| Dipropylene glycol methyl ether | - | - | - | 6.0 |
| Polyester solution (I) | 2.4 | 2.4 | 2.4 | 2.4 |

The viscosity behavior of the inventive (examples 1 and 2) and of the noninventive (comparative experiments C1 and C2) aqueous basecoat materials was measured under 5 different shear rates. The results can be found in tab. 2.

Table 2: The viscosity behavior of the inventive (examples 1 and 2) and of the noninventive (comparative experiments C1 and C2) aqueous basecoat materials

| Shear rate (s^{-1}) | Viscosity (mPas): | | | |
|-------------------------|--------------------------|-----|-----------|-----|
| | Comparative experiments: | | Examples: | |
| | C1 | C2 | 1 | 2 |
| 34 (outgoing curve) | 360 | 220 | 355 | 350 |
| 1000 | 73 | 73 | 73 | 73 |
| 34 (return curve) | 250 | 180 | 245 | 235 |

The values from table 2 demonstrate that the aqueous basecoat materials of examples 1 and 2 and of comparative experiments C1 and C2 had a comparable (comparative experiment C2 on the one hand and examples 1 and 2 and comparative experiment C1 on the other) or identical (examples 1 and 2 and comparative example C1) viscosity behavior.

Examples 3 and 4 and comparative experiments C3 and C4

Testing of the inventive (examples 3 and 4) and of the
noninventive (comparative experiments C3 and C4)
5 aqueous basecoat materials for their action against the
formation of optical defects

For example 3, the inventive aqueous basecoat material
of example 1 was used.

10

For example 4, the inventive aqueous basecoat material
of example 2 was used.

15

For comparative experiment C3, the noninventive aqueous
basecoat material of comparative experiment C1 was
used.

20

For comparative experiment C4, the noninventive aqueous
basecoat material of comparative experiment C2 was
used.

The test panels of examples 3 and 4 and of comparative
experiments C3 and C4 were prepared in accordance with
the following general instructions:

25

Steel panels coated cathodically with a commercial
electrocoat material (electrocoat with a thickness of
18-22 μm) were first coated with a commercial filler
from BASF Coatings AG, using a cup-type gun, and baked.

This gave a surfacer with a thickness of from 35 to 40 μm . Atop the surfacer there were then applied, in the same way, the inventive and the noninventive aqueous basecoat materials (cf. table 1), which were
5 predried at 80°C for 10 minutes. Following the cooling of the panels, a coat of commercial two-component high-solids clearcoat material from DuPont was applied in each case, predried at room temperature for 10 minutes, and then crosslinked together with the basecoats at
10 140°C for 45 minutes. This gave basecoats with a thickness of 15 μm and clearcoats with a thickness of 44 μm .

1. Light spots

15 In the wet sanding of defects in an original finish or in a surfacer, water droplets remain on the parts of the body that are to be overcoated with basecoat and clearcoat. These water droplets are made up of water, abrasion dust from clearcoat and/or surfacer, and
20 residues of the abrasive paper. Following the drying of these water droplets and subsequent coating with the basecoat and clearcoat, the sites of the dried-out water are visible as light (-colored) spots.

25 In order to simulate this effect, abrasion water droplets (deionized water + abrasion dust from surfacer and clearcoat + abrasive paper from Plochmann, softened in this composition) of various sizes were applied to

the respective test panels, dried at room temperature and coated with the respective basecoat materials employed for the original finish and described in table 1 and with the two-component high-solids clearcoat material from DuPont. The resulting color differences in the coatings (light spots) were assessed visually. The results obtained can be found in table 3.

2. Polishing spots

10

Polishing sites were produced on the test panels using a red/white felt pad (Buffing Pad from 3M, No. 049-5765) and the gray polishing paste from 3M (No. 029-2778). In the subsequent coating with the basecoat materials described in table 1 and the abovementioned clearcoat material, these polishing sites were clearly visible on account of their different color. The respective difference in color was determined visually. The results obtained can be found in table 3.

3. Abrasion spots

Using an abrasive paper from Plochmann with a grade of 2000, both a round and a cross-shaped abrasion site were applied to the test panels. These abrasion sites were coated with the basecoat materials described in table 1 and with the abovementioned clearcoat material.

The respective color difference was determined visually. The results obtained can be found in table 3.

The color difference, i.e., the obviousness of the defects, was scored as follows:

Rating meaning

- 1 defects not visible
- 2 defects very slightly visible
- 3 defects slightly visible
- 4 defects markedly visible
- 5 defects very markedly visible

Table 3: The effect of the inventive (examples 3 and 4) and of the noninventive (comparative experiments C3 and C4) aqueous basecoat materials on the formation of optical defects

| Optical defects | Comparative experiments: | | Examples: | |
|-----------------|--------------------------|----|-----------|-----|
| | C3 | C4 | 3 | 4 |
| Light spots | 4 | 5 | 2 | 2 |
| Polishing spots | 4 | 5 | 4 | 2-3 |
| Abrasion spots | 3-4 | 4 | 2-3 | 2 |

20

The results demonstrate that by means of the aqueous basecoat materials of the invention the formation of optical defects can be effectively suppressed.

An additional improvement results from the use of dipropylene glycol monoalkyl ether. The comparison of the results in table 3 with the aqueous basecoat material viscosity behavior shown in the overview in 5 table 2 underlines the fact that said behavior, surprisingly, is not responsible for the advantageous effect of the aqueous basecoat materials of the invention.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
2194
2195
2196
2197
2198
2199
2200
2201
2202
2203
2204
2205
2206
2207
2208
2209
2210
2211
2212
2213
2214
2215
2216
2217
2218
2219
2220
222

Claims

1. Use of polyurethane-based associative thickeners and/or dipropylene glycol monoalkyl ethers for
5 suppressing optical defects in multicoat color and/or effect paint systems or their refinishes.
2. The use as claimed in claim 1, characterized in that the multicoat color and/or effect paint
10 system and/or its refinish comprise or comprises at least one basecoat and at least one clearcoat.
3. The use as claimed in claim 2, characterized in that the basecoat is produced from an aqueous
15 basecoat material.
4. The use as claimed in claim 3, characterized in that the aqueous basecoat material is
polyurethane-based.
20
5. The use as claimed in any of claims 2 to 4, characterized in that the polyurethane-based associative thickener and/or dipropylene glycol
monoalkyl ether is or are present in the basecoat
25 material or materials.
6. The use as claimed in any of claims 2 to 5, characterized in that the polyurethane-based

associative thickener and dipropylene glycol monoalkyl ether are present in the basecoat material or materials.

5 7. The use as claimed in any of claims 1 to 5, characterized in that the optical defects comprise

10 - light-colored spots, introduced by dried-up liquid residues and/or abrasion dust residues, which remain after the abrading of defects in a multicoat color and/or effect paint system or in a surfacer that is to be coated with a multicoat color and/or effect paint system; and

15 - polishing spots, induced by the polishing of defects in a multicoat color and/or effect paint system which is performed for the purpose of refinishing the multicoat color and/or effect paint system.

20

8. The use as claimed in any of claims 3 to 7, characterized in that the aqueous basecoat material comprises

25 (A) at least one water-soluble or -dispersible polyurethane,

(B) at least one crosslinking agent,

(C) at least one color and/or effect pigment,

(D) at least one neutralizing agent,

5 (E) at least one inorganic thickener, and

(F) at least one dipropylene glycol monoalkyl ether.

10 9. The use as claimed in claim 8, characterized in that the aqueous basecoat material comprises

(G) at least one polyurethane-based associative thickener.

15

10. The use as claimed in any of claims 3 to 7, characterized in that the aqueous basecoat material comprises

20 (A) at least one water-soluble or -dispersible polyurethane,

(B) at least one crosslinking agent,

25 (C) at least one color and/or effect pigment,

(D) at least one neutralizing agent,

(E) at least one inorganic thickener,

(G) at least one polyurethane-based associative thickener,

5 (H) if desired, at least one water-soluble or -dispersible polyacrylate resin prepared in the presence of a water-soluble or -dispersible polyurethane, and

10 (I) at least one water-soluble or -dispersible polyester resin.

11. The use as claimed in claim 10, characterized in that the aqueous basecoat material comprises

15 (F) at least one dipropylene glycol monoalkyl ether.

12. The use as claimed in any of claims 8, 9 and 11, characterized in that the aqueous basecoat material, based on its overall weight, contains from 0.5 to 11% by weight of dipropylene glycol monoalkyl ethers (F).

25 13. The use as claimed in any of claims 9 to 12, characterized in that the aqueous basecoat material, based on its overall weight, contains from 0.1 to 4% by weight of at least one polyurethane-based associative thickener (G).

14. The use as claimed in any of claims 3 to 13,
characterized in that the aqueous basecoat
material comprises

5

(J) at least one additive.

15. An aqueous basecoat material comprising

10 (A) at least one water-soluble or -dispersible
polyurethane,

(B) at least one crosslinking agent,

15 (C) at least one color and/or effect pigment,

(D) at least one neutralizing agent,

(E) at least one inorganic thickener, and

20

(F) at least one dipropylene glycol monoalkyl
ether.

16. The aqueous basecoat material as claimed in claim
25 15, characterized in that it comprises

(G) at least one polyurethane-based associative
thickener.

17. An aqueous basecoat material comprising

(A) at least one water-soluble or -dispersible
polyurethane,

5

(B) at least one crosslinking agent,

(C) at least one color and/or effect pigment,

10

(D) at least one neutralizing agent,

(E) at least one inorganic thickener,

15

(G) at least one polyurethane-based associative
thickener,

(H) if desired, at least one water-soluble or -
dispersible polyacrylate resin prepared in
the presence of a water-soluble or -
dispersible polyurethane, and

20

(I) at least one water-soluble or -dispersible
polyester resin.

25 18. The aqueous basecoat material as claimed in claim
17, characterized in that it comprises

(F) at least one dipropylene glycol monoalkyl
ether.

19. The aqueous basecoat material as claimed in any of claims 15, 16 and 18, characterized in that it, based on its overall weight, contains from 0.5 to 11% by weight of dipropylene glycol monoalkyl ethers.

20. The aqueous basecoat material as claimed in any of claims 16 to 19, characterized in that it, based on its overall weight, contains from 0.1 to 4% by weight of at least one polyurethane-based associative thickener.

21. The aqueous basecoat material as claimed in any of claims 15 to 20, characterized in that it comprises

(J) at least one additive.

22. The use of the aqueous basecoat material as claimed in any of claims 15 to 21 for the original coating of motor vehicle bodies, industrial components, including electrical components, coils, and packaging, plastics or furniture, or for the refinish of multicoat color and/or effect paint systems present thereon.

23. Multicoat color and/or effect paint systems comprising at least one basecoat producible from

an aqueous basecoat material as claimed in any of
claims 15 to 21.

ABSTRACT

Use of associative thickeners based on polyurethane and/or dipropylene glycol monoalkyl ethers for suppressing defects in color and/or effect multicoat paint systems, or their touch-up paints.

| | | | |
|---|--|----------------------|------------------------|
| DECLARATION FOR UTILITY OR DESIGN PATENT APPLICATION (37 CFR 1.63) | | Attorney Docket No. | IN - 5562 |
| | | First Named Inventor | Ines MANGELS et al. |
| <input checked="" type="checkbox"/> Declaration Submitted with initial Filing or <input type="checkbox"/> Declaration Submitted after initial Filing (surcharge (37 CFR 1.16 (e)) required) | | COMPLETE IF KNOWN | |
| | | Application Number | |
| | | Filing Date | Monday, March 11, 2002 |
| | | Group Art Unit | |
| | | Examiner Name | |

As below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

USE OF ASSOCIATIVE THICKENERS BASED ON POLYURETHANE AND/OR DIPROPYLENE GLYCOL
 MONOALKYL ETHERS IN COLOURED AND/OR DECORATIVE EFFECT MULTI-LAYERED
 LACQUERS

(Title of the Invention)

The specification of which:

☒ Is attached hereto
☒ Was filed on **31. August 2000** as United States Application or PCT International Application Number **PCT/EP00/08503**
 and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56, including for continuation-in-part applications, material information which became available between the filing date of the prior application and the national or PCT international filing date of the continuation-in-part application

I hereby claim foreign priority benefits under 35, U.S.C. § 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate or 365 (a) of any PCT international application(s) designating at least one country other than the United States of America listed below and have also identified below, by checking the box, any foreign application(s) for patent or inventor's certificate, or any PCT international application(s) having a filing date before that of the application on which priority is claimed.

| Prior Foreign Application Number(s) | Country | Foreign Filing Date DATE/MONTH/YEAR | Priority Not Claimed | Certified Copy Attached? | |
|-------------------------------------|---------|-------------------------------------|--------------------------|--------------------------|--------------------------|
| 199 45 574.0 | GERMANY | 23. September 1999 | <input type="checkbox"/> | <input type="checkbox"/> | <input type="checkbox"/> |
| | | | <input type="checkbox"/> | <input type="checkbox"/> | <input type="checkbox"/> |

Additional foreign application number are listed on a supplemental priority data sheet PTO/SB/02B attached hereto:

I hereby claim the benefit under 35 U.S.C 119(e) of any United States provisional application(s) listed below:

| APPLICATION NUMBER(S) | FILING DATE |
|-----------------------|-------------|
| | |

☐ Additional provisional application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto

DECLARATION —

Utility or Design Patent Application

POWER OF ATTORNEY

☒ I hereby appoint the practitioner(s) associated with the Customer Number provided below to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith

☒ Customer Number or Bar Code Label

26922

PATENT TRADEMARK OFFICE

or ☐ Correspondence address below

County

United States of America

Telephone

(248) 948-2019

Fax

(248) 948-2093

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Name OF SOLE OR FIRST INVENTOR:

☐ A petition has been filed for this unsigned inventorGiven Name
(first and middle (if any))

Ines

Family Name
or Surname

MANGELS

Inventor's
Signature

Date

31.01.2002

Residence: City

48165 Münster

State

Germany

Country

Federal Republic
of Germany

Citizenship

German

Mailing Address

Pinienweg 21

City

48165 Münster

State

Germany

Zip

DECLARATION —

Utility or Design Patent Application

POWER OF ATTORNEY

☒ I hereby appoint the practitioner(s) associated with the Customer Number provided below to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith

☒ Customer Number or Bar Code Label



26922

PATENT-TRADEMARK OFFICE

or ☐ Correspondence address below

| | | | | | |
|--------|--------------------------|-----------|----------------|-----|----------------|
| County | United States of America | Telephone | (248) 948-2019 | Fax | (248) 948-2093 |
|--------|--------------------------|-----------|----------------|-----|----------------|

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

| | | | | | | | |
|---|---------------------|------------------|---------|--|-----------------------------|-------------|--------|
| Name OF SECOND INVENTOR: <u>J. Josten</u> | | | | A petition has been filed for this unsigned inventor | | | |
| Given Name <u>Karl-Heinz</u> | | | | Family Name or Surname <u>JOSTEN</u> | | | |
| (first and middle (if any)) | | | | Date <u>05.06.2002</u> | | | |
| Inventor's Signature <u>Josten</u> | | | | | | | |
| Residence: City | 97209 | State | Germany | Country | Federal Republic of Germany | Citizenship | German |
| Mailing Address | | Brusseler Str. 8 | | | | | |
| City | 97209 Veitshöchheim | State | Germany | Zip | | | |

DECLARATION —

Utility or Design Patent Application

POWER OF ATTORNEY

☒ I hereby appoint the practitioner(s) associated with the Customer Number provided below to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith

| | | | |
|---|--|----|---|
| <input checked="" type="checkbox"/> Customer Number or Bar Code Label |  26922 PATENT-TRADEMARK OFFICE | or | <input type="checkbox"/> Correspondence address below |
|---|--|----|---|

| | | | | | |
|--------|--------------------------|-----------|----------------|-----|----------------|
| County | United States of America | Telephone | (248) 948-2019 | Fax | (248) 948-2093 |
|--------|--------------------------|-----------|----------------|-----|----------------|

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

| | |
|--|--|
| Name of Additional Joint Inventor, If any: <input type="checkbox"/> A petition has been filed for this unsigned inventor | |
| Given Name (first and middle (if any)) <u>Udo</u> | Family Name or Surname <u>NENNER</u> |
| Inventor's Signature <u>Udo Nenner</u> | Date <u>06.02.2002</u> |
| Residence: City <u>97877 Wertheim</u> State <u>Germany</u> | Country <u>Federal Republic of Germany</u> Citizenship <u>German</u> |
| Mailing Address <u>Am Mühlacker 3</u> | |
| City <u>97877 Wertheim</u> State <u>Germany</u> | Zip <u></u> |

DECLARATION —

Utility or Design Patent Application

POWER OF ATTORNEY

☒ I hereby appoint the practitioner(s) associated with the Customer Number provided below to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith

☒ Customer Number or Bar Code Label



26922

PATENT-TRADEMARK OFFICE

or ☐ Correspondence address below

| | | | | | |
|--------|--------------------------|-----------|----------------|-----|----------------|
| County | United States of America | Telephone | (248) 948-2019 | Fax | (248) 948-2093 |
|--------|--------------------------|-----------|----------------|-----|----------------|

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

| | | | | | |
|---|----------------------|--|---------------------------|--|--|
| Name of Additional Joint Inventor, If any: <input type="checkbox"/> | | A petition has been filed for this unsigned inventor | | | |
| Given Name (first and middle [if any]) <u>Egon</u> | | Family Name or Surname <u>WEGNER</u> | | | |
| Inventor's Signature <u>[Signature]</u> | | Date <u>11.02.2002</u> | | | |
| Residence: City <u>97209</u> | State <u>Germany</u> | Country <u>Federal Republic of Germany</u> | Citizenship <u>German</u> | | |
| Mailing Address <u>Martinstr. 8</u> | | | | | |
| City <u>97209 Veitshöchheim</u> | State <u>Germany</u> | Zip | | | |

DECLARATION —

Utility or Design Patent Application

POWER OF ATTORNEY

☒ I hereby appoint the practitioner(s) associated with the Customer Number provided below to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith

☒ Customer Number or Bar Code Label



26922

PATENT-TRADEMARK OFFICE

or ☐ Correspondence address below

| | | | | | |
|--------|--------------------------|-----------|----------------|-----|----------------|
| County | United States of America | Telephone | (248) 948-2019 | Fax | (248) 948-2093 |
|--------|--------------------------|-----------|----------------|-----|----------------|

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

| | | | | | | | |
|---|--------------|-----------|----------------|---|------------------------------------|-------------|---------------|
| Name of Additional Joint Inventor, If any: <input type="checkbox"/> | | | | A petition has been filed for this unsigned inventor <input type="checkbox"/> | | | |
| Given Name (first and middle if any) Ekkehard | | | | Family Name or Surname SAPPER | | | |
| Inventor's Signature <i>Ekkehard Sapper</i> | | | | Date 7. Februar 2002 | | | |
| Residence: City | 97222 Rimpar | State | Germany | Country | Federal Republic of Germany | Citizenship | German |
| Mailing Address | | Austr. 55 | | | | | |
| City | 97222 Rimpar | State | Germany | Zip | | | |

DECLARATION —

Utility or Design Patent Application

POWER OF ATTORNEY

☒ I hereby appoint the practitioner(s) associated with the Customer Number provided below to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith

☒ Customer Number or Bar Code Label



26922

PATENT-TRADEMARK OFFICE

or

Correspondence address below

County United States of America

Telephone

(248) 948-2019

Fax

(248) 948-2093

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Name of Additional Joint Inventor, if any:



A petition has been filed for this unsigned inventor

Given Name
(first and middle [if any])

Nicola

Family Name
or Surname

ZARSE

Inventor's
Signature

Nicola Zarse

Date

04.07.02

Residence: City

48165 Münster

State

Germany

Country

Federal Republic
of Germany

Citizenship

German

Mailing Address

Kardinalstr. 16

City

48165 Münster

State

Germany

Zip